

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

21003762-  
İNG

02-21

**TEST RESULTS**

**TENSILE STRENGTH; EN 29073-3:1996**

Instron 5969 (Load: 50 kN), Strip Method.  
Speed: 100 mm/min $\pm$ 10, Gauge length 200 mm.  
Pre-load was not applied. Without wetting samples.  
The average results are given for weft and warp direction of five samples  
Performed in the conditioned room (20 $\pm$ 2°C-65% $\pm$ 4).

**Critical area**

**Wet ;**

**RESULT**

65,2 N

**Weft**

143,9 N

**Warp**

**REQUIREMENT**

$\geq$  20N (Wet )

$\geq$  20N (Wet )

**BURSTING STRENGTH;; ISO 13938-1:1999**

SDL ATLAS M229 tester. Test area: 30.5 mm diameter  
Rate of increase in volume; 29 cm<sup>3</sup>/min.  
The average results are given of five samples.  
Performed in the conditioned room (20 $\pm$ 2°C-65% $\pm$ 4).  
**Critical area**

**RESULT**

196,0 kPa

**Dry ;**

86,0 mm

**Height at Burst\***

**REQUIREMENT**

$\geq$  40 kPa (Dry)

**ZENMED TIBBİ CİHAZLAR  
VE SAĞLIK ÜRÜNLERİ SAN. VE TİC. LTD.ŞTİ.**  
Mahmutbey Mah. 2567.Sk. No:1 İş Yeri No:11,21  
Bağcılar / İSTANBUL / TÜRKİYE  
Tel: 0212 445 45 25 Tic.Sic.No: 794704  
Güneşli V.D.: 997 067 1942