




Eco-245

65% RECYCLED POLYESTER /
35% RECYCLED COTTON /
245 GSM / TWILL 3/1



Fabric name	Eco-245
Fabric weight	245 ± 5 gsm
Composition	65% Recycled Polyester, 35% Recycled Cotton
Full width	152 ± 2 cm
Weave	twill 3/1
Finishes	WR
Area of use	construction and transport sectors work wear

Washing instruction



Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1600	450
2	Tearing strength, N	ISO 13937-3:2000	50	23
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 30 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010		4
	Colour staining	ISO 105-C06:2010		3
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change			4
	Colour staining			4
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry			3-4
	Wet			2-3
9	Colour Fastness To Light	ISO 105-B02:2013		> 4

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com



STANDARD
100

BEWO 084394
TESTEX

This certificate BEWO 084394 is valid until
15.08.2025.

SUPPORTING DOCUMENTS

- ✓ Test report : BJO15 245163.1
- ✓ Declaration of conformity in accordance with
EN ISO 17050-1 as required by OEKO-TEX
- ✓ OEKO-TEX Terms of Use (ToU)

Matz Bachmann
Managing Director

Dijana Ajdinovic
Ecology Team Leader

Zurich, 2024-07-29