



## TECHNICAL DATA SHEET

### PHOTOCOPY PAPER (ALLCOPY)

Grade : ALL080ALK2

#### Physical Parameters

	Reference	Target	Minimum	Maximum
Basis Weight, $g/m^2$	ISO 536	80	78	82
Thickness, $\mu m$	ISO 534	105	103	107
Moisture, %	ISO 287	4,5	4,0	5,0
Breaking Length MD, $m$	ISO 1924-2	--	4000	--
Breaking Length CD, $m$	ISO 1924-2	--	2000	--
COBB (60s), $g/m^2$	ISO 435	24	20	28

#### Optical Parameters

	Reference	Target	Minimum	Maximum
Whiteness, $CIE$	ISO 11475	148	143	150
Brightness D65, %	ISO 2470	--	100	--
Yellowness	ISO 2470	-25,0	-27,0	-23,0

01.11.2020 / Rev:00 Page 1/2



ALKİM KAGIT SANAYİ VE TİCARET A.Ş.