

TESTING CENTER OF CABLE PRODUCTS

Autogennaya str. 7, Kharkov, 61099, Ukraine,
Phone: +38 057 754 52 75
E-mail: lab@yuzhcable.com.ua

Accredited by:
National Accreditation Agency of Ukraine - A national accreditation body of Ukraine
Certificate of Accreditation № 20353 dated January 16, 2024; Valid until January 15, 2029

TEST REPORT

Report reference number 17
Tested by Andrew Konoplev, Alina Shurupova
Approved by Nikolay Zykov
Date of issue 30-Jan-26
Testing laboratory Testing center of cable products,
Address Autogennaya str. 7, Kharkov, 61099, Ukraine,
Phone: +38 057 754 52 75, E-mail: lab@yuzhcable.com.ua
Manufacturer YUZH CABLE WORKS, PJSC
Address Autogennaya str. 7, Kharkov, 61099, Ukraine
Standard TY Y 31.3-00214534-018-2003
Test procedure Tests
Cable type ABBГнр-LS 3×4
Trade mark YUZH CABLE
Rating(s) Uo/U 0,66/1,0
Dates of receipt of test item 19-Jan-26
Dates of performance of tests From 20-Jan-26 to 29-Jan-26
Summary of test results PASS

Ref No.	Tests	Prescribed	Observed			Verdict
1	Electrical tests					
			BN	BK	GY	Pass
1.1	Resistance of conductors (Ω/km)	Max. 7,41	7,36	7,34	7,36	Pass
1.2	Volume resistivity of insulation at 20°C (Ω·cm)	Min. 10 ¹³	7,17	7,21	7,32	Pass
	at 70°C (Ω·cm)	Min. 10 ¹⁰	5,85	6,15	6,08	Pass
1.3	Voltage test 2,4 kV/4 h	No breakdown of the insulation	No breakdown of the insulation			Pass
2	Non-electrical tests					
2.1	Measurement of thickness of insulation - value (mm)	1,0 _{-0,2}	1,02	1,04	1,05	Pass
2.2	Measurement of thickness of sheath - value (mm)	1,8	1,92			Pass

TESTING CENTER OF CABLE PRODUCTS

Autogennaya str. 7, Kharkov, 61099, Ukraine,
 Phone: +38 057 754 52 75
 E-mail: lab@yuzhcable.com.ua

Accredited by:
 National Accreditation Agency of Ukraine - A national accreditation body of Ukraine
 Certificate of Accreditation № 20353 dated January 16, 2024; Valid until January 15, 2029

Ref No.	Tests	Prescribed	Observed			Verdict
2.3	Mechanical properties of insulation					
	<i>Without ageing:</i>					
	Tensile strength (N/mm ²)	Min. 12,5	13,8	14,2	14,0	Pass
	Elongation-at-break (%)	Min. 150	290	300	295	Pass
	<i>After ageing in air oven:</i>					
	Duration (h) / Temperature (°C)	168 / (100±2)				
	Tensile strength (N/mm ²)	Min. 12,5	13,0	13,3	13,1	Pass
	Elongation-at-break (%)	Min. 150	268	276	272	Pass
	Tensile strength variation (%)	Max. ±25	-5,5	-6,2	-6,7	Pass
	Elongation-at-break variation (%)	Max. ±25	-7,5	-8,0	-7,7	Pass
	<i>Pressure test at high temperature</i>					
	Duration (h) / Temperature (°C)	4 / (80±2)				
Median of the depth of indentation (%)	Max. 50	20	22	20	Pass	
<i>Heat shock test</i>						
Duration (h) / Temperature (°C)	1 / (150±3) No cracks	No cracks	No cracks	No cracks	Pass	
2.4	Mechanical properties of sheath					
	<i>Without ageing:</i>					
	Tensile strength (N/mm ²)	Min. 12,5		14,3		Pass
	Elongation-at-break (%)	Min. 150		280		Pass
	<i>After ageing in air oven:</i>					
	Duration (h) / Temperature (°C)	168 / (100±2)				
	Tensile strength (N/mm ²)	Min. 12,5		13,1		Pass
	Elongation-at-break (%)	Min. 150		254		Pass
	Tensile strength variation (%)	Max. ±25		-8,5		Pass
	Elongation-at-break variation (%)	Max. ±25		-9,2		Pass
	<i>Heat shock test</i>					
	Duration (h) / Temperature (°C)	1 / (150±3) No cracks	No cracks	No cracks	No cracks	Pass
<i>Pressure test at high temperature</i>						
Duration (h) / Temperature (°C)	6 / (80±2)					
Median of the depth of indentation (%)	Max. 50		27		Pass	

TESTING CENTER OF CABLE PRODUCTS

Autogennaya str. 7, Kharkov, 61099, Ukraine,
 Phone: +38 057 754 52 75
 E-mail: lab@yuzhcable.com.ua

Accredited by:
 National Accreditation Agency of Ukraine - A national accreditation body of Ukraine
 Certificate of Accreditation № 20353 dated January 16, 2024; Valid until January 15, 2029

Ref No.	Tests	Prescribed	Observed			Verdict
2.5	Additional ageing test on pieces of completed cables	168 / (100±2)				
	Duration (h) / Temperature (°C)					
	<i>mechanical properties of insulation:</i>					
	Tensile strength variation (%)		Max. ±25	-7,2	-6,8	-6,9
	Elongation-at-break variation (%)	Max. ±25	-8,5	-8,2	-7,0	Pass
	<i>mechanical properties of sheath:</i>					
	Tensile strength variation (%)	Max. ±25		-8,0		Pass
	Elongation-at-break variation (%)	Max. ±25		-9,2		Pass
2.6	Vertical flame propagation					
	- time of application of flame s	60				
	- distance between the lower edge of the top support and the onset of charring mm	Min 50		365		Pass
	- distance between the lower edge of the top support and the charring extends downwards mm	Max 540		508		Pass

Nikolay Zykov,
 Head of TCCP

Andrew Konoplev,
 Head of the Laboratory of electrical tests

Alina Shurupova,
 Head of Laboratory of promising developments

