




KLAR Professional Chit Extra Soft		Chit Extra Soft								
Descriere:	KLAR Professional Chit Extra Soft este un chit poliesteric, aplicabil pe toate suprafetele de metal. Produsul, cu o aderenta excelenta la substrat (tabla galvanizata, aluminiu, fibra de sticla) este foarte moale, se aplica si se slefuieste usor.									
Produse:	KLAR Professional Chit Extra Soft Intaritor									
Structura de baza:	KLAR Professional Chit Extra Soft Intaritor	rasini poliesterice								
Tipuri substrat:	• Otel, tabla zincata, aluminiu • Fibra de sticla									
Pregatirea suprafetei:	Suprafetele trebuie sa fie curate, uscate, degresate si slefuite. Amestecati bine chitul cu intaritorul, tinand cont de temperatura camerei. • Degresare • Amestec cu Intaritor  D-AS  <table><tr><th>Temperatura (°C)</th><th>Intaritor – greutate (%)</th></tr><tr><td>5 - 10</td><td>2.5 – 3</td></tr><tr><td>10 - 20</td><td>1.5 – 2.5</td></tr><tr><td>➤ 20</td><td>1 - 2</td></tr></table> • Pot-life: 4 – 7 min. la 20° C.		Temperatura (°C)	Intaritor – greutate (%)	5 - 10	2.5 – 3	10 - 20	1.5 – 2.5	➤ 20	1 - 2
Temperatura (°C)	Intaritor – greutate (%)									
5 - 10	2.5 – 3									
10 - 20	1.5 – 2.5									
➤ 20	1 - 2									
Aplicare:	Aplicati unul sau mai multe straturi in functie de grosimea dorita. A se aplica astfel incat chitul sa adere omogen pe suport.  • Gorsimea de strat recomandata: 200 – 900 µm.									
Uscare:	• Uscare la aer: 20 – 30 min./ 20° C  • Slefuire/ uscat: P 80, P 120, P 220 									



KLAR Professional Chit Extra Soft		Chit Extra Soft
VOC:	241.11 g/l	
Termen de valabilitate:	KLAR Professional Chit Extra Soft	12 luni
Ambalare:	KLAR Professional Chit Extra Soft	Cutii metalice 1.35 kg
Culoare:	Galben	
Masuri SSM si SU:	Doar pentru uz profesional.(Vezi fisa de securitate). Toate operatiile de manipulare, transport, depozitare, utilizare, distrugere a reziduurilor se vor face aplicand cu strictete normele SU, normele de SSM, in functie de caracterizarea produsului.	