

TECHNICAL DATA SHEET

MANUFACTURER: INDUS MEDICARE LIMITED – HYDERABAD

COUNTRY OF MANUFACTURER: INDIA

SPECIFICATION: ISO 4074: 2015

TYPE OF PRODUCT: NATURAL RUBBER MALE LATEX CONDOMS 53MM (EXTRA STRONG)

| SL.NO | CRITERIA / TEST | INSPECTION LEVEL | AQL | SPECIFICATIONS |
|-------|---|--|----------------------------------|--|
| 1. | DIMENSIONS LENGTH (L), WIDTH (W) AND THICKNESS (T) | 13 PCS | 0 | L = 180 - 200 mm W = 52 - 54 mm $T = \ge 0.1 \text{ mm}$ |
| 2. | BURSTING VOLUME AND PRESSURE BEFORE OVEN CONDITIONING | G – 1 | 1.5 ACCEPT- 10 REJECT - 11 | B.V = min.18.0 Ltrs. B.P = min. 1.0 KPa. |
| 3. | FREEDOM FROM HOLES | G – I (min. 315pcs) | 0.25 ACCEPT-2 REJECT-3 | AS PER AQL |
| 4. | VISUAL DEFECTS | G – I (min. 315pcs) | 0.4 ACCEPT-3 REJECT-4 | AS PER AQL |
| 5. | VISIBLY OPEN SEALS | G-I (min. 315pcs) | 0.4 ACCEPT- 3 REJECT - 4 | AS PER AQL |
| 6. | PACKAGE INTEGRITY | S – 3 | 2.5 ACCEPT-2 REJECT- 3 | AS PER AQL |
| 7. | LUBRICANT PLUS POWDER (SILICONE OIL) | S-2 | 4.0 ACCEPT- 1 REJECT- 2 | Min.350 mg |
| 8. | PACKAGING & LABELING | 13 Individual packs + 13 Consumer packs | 0 | AS PER AQL |

BV- Burst Volume

BP- Burst Pressure

AQL- Acceptance Quality Limit

Note:

a) ISO 2859-1: Sampling procedure for inspection by attributes.

b) Above acceptance Limit is applicable for the Lot / Batch Size (1,50,000 to 5,00, 000 pieces)