



SINCE 1965



## COPIER BOND TECHNICAL SPECIFICATIONS OF PHOTOCOPY PAPER

### DIMENSION



### PHYSICAL PARAMETERS

|                  | UNIT                             | SPECIFICATIONS | REFERENCE           |
|------------------|----------------------------------|----------------|---------------------|
| WEIGHT           | g/m <sup>2</sup>                 | 80 ± %4        | TS 3122 EN ISO 536  |
| THICKNESS        | Micron (µm)                      | Min.100        | TS EN ISO 534:2011  |
| MOISTURE         | %                                | 3.8-5,6        | TS EN ISO 287       |
| COBB60           | g/m <sup>2</sup>                 | 15 – 30        | TS 609 EN ISO 20535 |
| WHITENESS        | CIE                              | 160 ± 3        | TS ISO 11475        |
| ROUGHNESS        | ml / min                         | 100 – 350      | TS ISO 5627         |
| BRIGHTNESS (ISO) | %                                | Min.105        | TS ISO 2470         |
| DIFFUSE OPACITY  | %                                | Min.91         | TS ISO 2471         |
| DIRT             | mm <sup>2</sup> / m <sup>2</sup> | Max.2          | TAPPI T 437         |



MADE IN TÜRKİYE