

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

CHAMÄLEON BITUM BRUSHABLE

Article number:	37101
General characteristics:	A unique blend of raw materials and special processing results in a product that has adhesion most common surfaces and gives excellent protection. The product should be used at temperatures between 15 °C and 35 °C. Bitum brushable gives excellent and durable protection
Application:	against rust and stone chip and has sound deadening properties. As Corrosion protective coating on metal surfaces, especially for application on cars such as the under side of floor panels, the inside of wheel arches on parts of the chassis, subframes, ect Do not apply on parts of the braking system
Properties:	or on part of the exhaust system. RC 112 can be applied on bare metal but for extra protection the use of an anti corrosion primer is advised. Extreme good barrier formation, Easy application, excellent anti sagging properties. Resistant to water, brine, acids and alkaline. Compatible with original PVC under coatings. Can only be over sprayed/painted with bitumen

product (not over paintable)





CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Technical information:		
Basis:	Oxidized bitumen, Fillers, softener, solvents en special additives	
Density:	1.34	
Solids:	74 %	
Viscosity:	Shear Thinning,	
Brookfield DVII	Ca. 100.000 mPas , sp6, 6 rpm.	
Color:	Black	
Smell:	Bitumen and turpentine	
Recommended layer thickness	700 mu wet, 400 mu dry	
/ Use	1 l per 1,4 m ²	
Salt spray test,	400 mu dry layer Rust: according DIN 53 210 → Ri 0	
SS DIN 50021, 500 Hours	Blistering: according DIN 53 209 → m0/g0	
Application temperature ° C:	10 to 25	
Temperature resistance of the	-50 to 80	
coating, ° C:		
Drying time: depends on	700 mu wet layer: Dust dry: ca. $3-5$ hours	
temperature, ventilation and	20° C + ventilation Touch dry: ca.14 – 20 hours	
layer thickness	Trough dry: ca 2 days	

Directions before use:

Stir the product before use, for Easy application it is recommended to warm up the product by the use of a water bath (a bucked with warm water) up to 40 °C. Surface must be dry and clean, free from dirt, rust, grease ect. (Dry) parts can be removed with aromatic solvents as white spirit, boiling point naphtha, xylene, turpentine etc.

Storage: Cool and dry

Shelf live: 2 years in original and unopened packaging

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.