

HI-KOTE C2S Gloss

Grammage	g/m ²	ISO536	90	105	115	130	150	157	170	200	230	250	270	300
Thickness	μm	ISO534	68	84	93	101	125	134	146	173	201	225	244	270
Brightness	%ISO	ISO2470	89	89	89	89	89	89	88.5	88.5	88.5	88.5	88.5	88.5
Opacity	%	ISO2471	92	93	94	96	97	98	98.5	98.5	98.5	98.5	98.5	98.5
Roughness	μm	ISO8791/4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.6
Gloss	%	T480	66	62	70	70	70	70	70	70	70	70	70	70

HI-KOTE C2S Matt

Grammage	g/m ²	ISO536	90	105	115	130	150	157	170	200	230	250	270	300
Thickness	μm	ISO534	75	96	108	122	146	153	168	200	230	250	270	285
Brightness	%ISO	ISO2470	89	90	90	90	90	90	88.5	88.5	88.5	88.5	88.5	88.5
Opacity	%	ISO2471	92	94	95	96	97	98	98.5	98.5	98.5	98.5	98.5	98.5
Roughness	μm	ISO8791/4	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0
Gloss	%	T480	35	30	30	30	30	30	30	30	30	30	30	30

Remarks: 90-157gsm is supplied from Gold East Paper Zhenjiang mill.

170-300gsm is supplied from Hainan Jinhai mill.