

Builder-240

100% COTTON 240 GSM / TWILL 3/1



Fabric name	Builder-240
Fabric weight	240 ± 5 gsm
Composition	100% Cotton
Full width	150 ± 2 cm
Weave	twill 3/1
Finishes	
Area of use	multi seasonal workwear
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1400	800
2	Tearing strength, N	ISO 13937-3:2000	29	22
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining	ISO 105-C06:2010	4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4	-5
	Colour staining		12	4
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		3	-4
	Wet		2	:-3
9	Colour Fastness To Light	ISO 105-B02:2013	>	4

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES ITALIA SRL



Test Report SL52035261736801TX Date:July 02,2020 Page 1 of 3

SHANGHAI XM GROUP LTD

ROOM 2403, ZHONGYI INTERNATIONAL BUILDING NO.1833, NORTH ZHONGSHAN ROAD, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric (BUILDER-240: (BUILDER-240,100% cotton, 240 gsm,

Order: XMT-20-023)

Composition : (A)100% cotton Sample Color : (A)Navy #C2

Proposed Care Instruction:

Sample Receiving Date : Jun 29, 2020

Testing Period : Jun 29, 2020 - Jul 02, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Hattie Chen (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-735) 8307 1443, or email: CN. Docchecke@ags.com/

3rdBuilding,No.889, Yishan Road, Xuhui District Shanghai, China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 f (8 t (86-21) 61402666 f (8

f (86-21) 64958763 w f (86-21) 64958763 e

www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report Test Result SL52035261736801TX

Date: July 02,2020

Page 2 of 3

Colour Fastness To Light

(ISO 105-B02:2014; Method 2 (Modified), use Xenon arc lamp, Exposure Cycle: A1, no flip-flop mode was used)

Comparison upto blue wool reference 4

- Unit (A)

Grade(B.W.S)

Colour Fastness To Rubbing

(ISO 105-X12:2016; Size of rubbing finger: 16mm dia.)

As Received

- Unit (A)
Dry Staining - 4
Wet Staining - 2-3

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Colour Fastness To Washing

(ISO 105-C06:2010; Test No.:C2S, Machine wash at 60℃ with 4 g/L ECE (B) and 1g/L Sodium Perborate with 25 Steel Balls)

· ·	Unit	(A)
Change in Shade		4-5
Staining On Multi-fibre Strip	oe .	
Acetate	2 .	4-5
Cotton	S 2	4-5
Polyamide	88	4-5
Polyester	9 2 0	4-5
Acrylic	85	4-5
Wool	(4)	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Dimensional Stability To Washing

(ISO 3759:2011/ISO 5077:2007/ISO 6330:2012; Using horizontal axis, front-loading type machine; Procedure No.6N, Machine Wash At 60℃; with 2kg total dry mass (Type I (100% Cotton) Ballast+ Specimen), 'ECE(A)' detergent+ Sodium Perborate+ TAED, Tumble Dry Low, Less Than 60℃)

After 1 Wash

- Unit (A)
Lengthwise % -2.9
Widthwise % -2.6

Remark: (+)Means Growth; (-)Means Shrinkage



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-735) 8307 1443, or email: CN. Docchecke@ags.com/

3rdBuilding,No.889, Yishan Road, Xuhui District Shanghai, China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report

SL52035261736801TX

Date: July 02,2020

Page 3 of 3

Tearing Strength

(ISO 13937-2:2000;)

-	Unit	(A)
Warp/Length Yarns Torn	N	29
Weft/Width Yarns Torn	N	22

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx.attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not excended as the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not excended as the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the full tilest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@ags.com

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666

f (86-21) 64958763

www.sgsgroup.com.cn e sgs.china@sgs.com SHANGHAI XM GROUP LTD. Room 2402-2403 Zhangyi International Commercial Plaza 1833 Zhangshan North Road Shanghai 200061 China



TESTEX AG: Swiss Teetle Testing Institute
Gotthardstraise 61
8002 Zurch
Switzerland

Certificate OEKO-TEX® STANDARD 100

SHANGHAI XM GROUP LTD.

is granted the OEKO-TEX* STANDARD 100 certification and the right to use the trademark.

SCOPE

Waven fabrics made of 100% CO, CO/PES, CO/CF, CO/PES/CF, CO/PA/CF (CF with anti-static function). piece-dyed (vat and disperse) (partly finished with flame retardant products accepted by OEKO-TEX "Tar with water, soil or all repellent finishing, woven fabric made of 100% PES, 100% PA, PES/EL, white, piece-dyed (disperse and acid) and finished, or woven fabric made of 100% PES, transfer printed (disperse) and finished, all with PAN coating undyed of piece-dyed line). fluorescent colours) knifted fabries (incl. fleece) and UV protection fabrics made of 100% PES, PES/CO, PES/CV. MAC/CO, MAC/CV, MAC/CO/PES, 100% PP, PP/PES, with or without spander (EL) and antistatic fibers; waven fabric in PA. PES, or mixed with EL, or with PU. TPU, PTFE membrane laminated, or boned fabrics of above with white/piece-dyed PES or PA knitted fabrics (incl. polar fleece) & finished (incl. water/oil-repel, antistain) (based an material pre-certified according to OEKO-TEX* STANDARD 100)

PRODUCT CLASS

II (products with direct contact to skin) - Annex 4

Further compliance information (REACH, SVHC, POP, 08)8401 etc.) can be found on celco-tex.com/en/faq.

The certificate is based on the test methods and requirements of the OEXO-TEX: STANDARD 100 that were in force at the time of evaluation.



This certificate BEWO 084394 is valid until 15.08.2024.

SUPPORTING DOCUMENTS

- Test report: BJ015 224706.1
- Declaration of conformity in accordance with EN ISO 17050-1 as required by OEKO-TEX
- ✓ OEKO-TEX Terms of Use (ToU)

Matz Bachmonn Managing Director

Dijana Ajdwovic (Ecology Team Leader

Zurich, 2023-07-21