



Cosmo-200

67% POLYESTER / 27% VISCOSE / 6% SPANDEX
200 GSM / TWILL 2/1



Fabric name	Cosmo-200
Fabric weight	200 ± 5 gsm
Composition	67% polyester, 27% viscose, 6% spandex
Full width	150 ± 2 cm
Weave	twill 2/1
Finishes	-
Area of use	Beauty and Health industry
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1000	970
2	Tearing strength, N	ISO 13937-3:2000	41	57
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 80 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	5	
	Colour staining	ISO 105-C06:2010	4-5	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		4	
9	Colour Fastness To Light	ISO 105-B02:2013	> 6	

* The values shown are indicative and may vary slightly from batch to batch.

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com





STANDARD
100

BEWO 084394
TESTEX

This certificate BEWO 084394 is valid until
15.08.2025.

SUPPORTING DOCUMENTS

- ✓ Test report : BJ015 245163.1
- ✓ Declaration of conformity in accordance with
EN ISO 17050-1 as required by OEKO-TEX®
- ✓ OEKO-TEX® Terms of Use (ToU)

Matz Bachmann
Managing Director

Dijana Ajdinovic
Ecology Team Leader

Zurich, 2024-07-29



