

# *WeldWrap™*

## Composite FRP Sleeve

(Part Numbers: W04-12 thru W60-18)

### Description

The WeldWrap™ Composite FRP Sleeve is a 10-layer rigid coil-shaped device used in conjunction with WrapMaster's – Adhesive & Putty systems to restore hoop-strength to degraded carbon steel piping. The WeldWrap™ Sleeve is 10-layers with the first two layers slotted .750 inches to fit a typical girth weld (custom configurations available upon request). WeldWrap™ is constructed from high tensile strength fiberglass strands incorporating a “magnetically detectable” material for Smart Pig Detection. The composite laminate is impregnated with a chemically resistant polyester resin and has a functional “male and female” surface of embossment. The “Diamond Lock” feature adds to the robustness of the WeldWrap™ Sleeve by providing a Dual Locking System - mechanical locking in addition to securing the system with the Adhesive.

**Recommended Repair Types:** “Blunted” defects associated with corrosion, dents or gouges in or near the girth weld with up to 80% wall loss on carbon steel piping (50% if defect is located in the girth weld zone). For use on ductile steel pipe for pipe grades up to API-5LX-80. Permanently repair of external defects. Temporarily repair of internal defects – longevity may be determined by the internal metal loss rate.

### Features

High Tensile Strength	Superior chemical resistance
Magnetically Detectable	Low Elongation
Dual Locking System	Excellent Durability

### Typical Properties

Tensile Strength	90 ksi	ASTM D3039
Tensile Modulus	5.0 msi	
Transverse Tensile Strength	12 ksi	ASTM D3039
Tensile Elongation (%)	1%	ASTM D638
Layer Thickness	.060 - .075	
Girth weld cut (custom cuts avail)	.750 in.	
Number of Layers	10	
Configured for Pipe Size(s)	4” thru 60”	
Standard Sleeve Widths	12” and 18”	
Max Operating Temperature	161°F/72°C per ASME PCC-2	



### Applying

WrapMaster's Installer Certification required for product use. Basic outline of application steps are 1) Pipe surface area should be clean, dry and free of contamination with an anchor pattern (NACE #3 or SA-2 ½). 2) Use Putty to fill cavity, girth weld and tented areas. 3) Apply Adhesive to pipe surface. 4) Attach WeldWrap™ Composite FRP Sleeve and apply adhesive while wrapping sleeve around pipe. 5) Tighten Sleeve and allow to cure for 2 hours.

### Storage

WeldWrap™ Composite FRP Sleeve should be stored in a dry shaded place at room temperature (77 °F).

---

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. Including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data is subject to change as WrapMaster deems appropriate. Appropriate engineering controls and precautions to be observed in using the material.

# *Wrapmaster<sup>TM</sup>* Adhesive System

## **Description**

Adhesive is a highly thixotropic, two component, methacrylate adhesive system. This adhesive forms a resilient bond and maintains its strength over a wide range of temperatures. Adhesive is suitable for bonding a variety of substrates with minimal surface preparation.

**Recommended Substrates:** PVC, polycarbonate, acrylic, aluminum, epoxy coated metal, ABS, carbon and stainless steel, and FRP.

## **Features**

Non-sagging gaps filled to 1 inch  
Little or no surface preparation  
Rapid room temperature cure 100% reactive

Superior impact and peel strength  
Offers excellent tolerance to off-ratio mixing  
Excellent environmental resistance

## **Typical Properties**

Tensile Lap Shear @ 77 °F	2,500-2,700	ASTM D1002
Tensile Lap Shear @ 180 °F	1,800-2,000	ASTM D1002
Tensile Elongation (%)	25-35	ASTM D638
Peel Strength (pli)	60	ASTM D3167
Shore D Hardness	75-80	
Bondline Thickness	.005-1.00	
Open Time @ 110 °F	40-45 minutes	16 : 1 Mix Ratio
Open Time @ 32 °F	160-180 minutes	4 : 1 Mix Ratio

## **Applying**

Bonding surface should be clean, dry, and free of contamination. Extensive surface preparation is not required for the adhesive system, a light scuffing with 100 grit sand paper or scotch bright pad and a solvent wipe. To assure maximum bond strength, surfaces must be mated within the adhesive's open time. Use enough material to completely fill the joint when parts are clamped.

## **Storage**

Adhesive should be stored in a cool, dry place when not used for a long period of time. Exposure above room temperature will reduce shelf life.

---

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. Including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data is subject to change as WrapMaster deems appropriate. Users should review the Safety Data Sheet (SDS) for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the SDS are available upon request.

# *Wrapmaster™*

## Filler Putty System

### **Description**

Putty Filler is a highly thixotropic, two component, system. The Filler Putty forms a high compressive strength, low shrinkage “load transfer” structure maintaining its strength over a wide range of temperatures. Putty is suitable for bonding a variety of substrates with minimal surface preparation.

**Recommended Substrates:** aluminum, epoxy coated metal, carbon and stainless steel, and FRP.

### **Features**

Non-sagging gaps filled to 1inch  
Little or no surface preparation  
Excellent environmental resistance

Superior compressive strength  
Rapid room temperature cure 100% reactive

### **Typical Properties**

Compressive Strength @ 77 °F	14,000	ASTM D1002
Compressive Strength @ 140 °F	10,000	ASTM D1002
Elongation (%)	< 1	ASTM D638
Shore D Hardness	> 80	
Bondline Thickness	.005-1.00	
Open Time @ 110 °F	40-50 minutes	2 : 1 Mix Ratio
Open Time @ 32 °F	220-240 minutes	2 : 1 Mix Ratio

### **Applying**

Bonding surface should be clean, dry, and free of contamination. Extensive surface preparation is not required for the Putty system, a light scuffing with 100 grit sand paper or scotch bright pad and a solvent wipe. To assure maximum bond strength, surfaces must be mated within the filler putty's open time. Use enough material to completely fill the joint when parts are clamped.

### **Storage**

Putty should be stored in a cool, dry place when not used for a long period of time. The shelf life is one year from the date of manufacture when stored in climate controlled environment.

---

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. Including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data is subject to change as WrapMaster deems appropriate. Users should review the Safety Data Sheet (SDS) for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the SDS are available upon request.

## *... Limitation of Warranty...*

1. All products are sold subject to Terms and Conditions of Sale by WrapMaster, Inc. A copy of these terms and conditions is available from the company at its office in Longview, Texas. All products are sold F.O.B. WrapMaster plant.
2. WrapMaster warrants that upon shipment, the goods will be (i) free from defects and workmanship and (ii) substantially in accordance with WrapMaster's standard specifications for the specific goods. If, within sixty (60) days after shipment, WrapMaster receives written notice of any defect in the material or workmanship of the specified goods, or the failure of the goods to meet WrapMaster's standard specifications therefore, WrapMaster will correct each such defect of failure, at WrapMaster's option, by either making available repaired goods or replacement goods.
3. All goods must be handled, stored, transported, installed, operated and maintained in accordance with WrapMaster's standard written instructions set forth herein or provided or approved in writing by WrapMaster. WrapMaster makes no warranties which extend to damage to the goods due to deterioration or wear occasioned by sunlight, chemicals, abrasion, corrosion, installation, operation or maintenance, abnormal conditions or temperature or other use of the goods above standard recommended uses or in an improper manner. WrapMaster's sole responsibility for defects in material and workmanship or goods and Customer's sole remedy hereunder will be as stated in Terms and Conditions of Sale of WrapMaster, Inc. Composite Systems are UV sensitive.
4. WRAPMASTER, IT'S SUBCONTRACTORS AND SUPPLIERS MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, AND SPECIFICALLY DISCLAIM ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR CONFORMITY WITH SAMPLES.
5. WRAPMASTER WILL NOT BE LIABLE FOR INCIDENTAL, INDIRECT, SPECIAL OR CONSEQUENTIAL DAMAGES, OR FOR LOST PROFITS, SAVINGS OR REVENUES OF ANY KIND, WHETHER OR NOT WRAPMASTER HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.
6. INSTALLATION OF WRAPMASTER PRODUCTS BY ANYONE OTHER THAN A CERTIFIED INSTALLER WILL VOID ANY AND ALL WARRANTIES SET FORTH HEREIN, IS DANGEROUS AND MAY CONSTITUTE A VIOLATION OF APPLICABLE GOVERNMENTAL REGULATIONS.