Mineral Services: +(203) 5728810, 5728812, 5728833

Alexandria Office: 8 Fahmi Wissa St, Louran

**Head Office** E-mail

: +(202) 27263000 : sgs\_egypt@sgs.com

Our Ref. NO.

: 2002255

Date

: 21st November 2017

Issuance

: Alexandria,

Report No.:190201/ Ore001294

Page: 1 of 1

# PRE-SHIPMENT REPORT

Pursuance of an order for inspection given to us by our principal "EGYPT SALT EXPORT"

Description of goods

: about 700 MT salt 1.4mm to 2mm.

Place of Sampling

: Client Store, 10th of Ramadan city.

**Date of Sampling** 

: 13.11.2017.

### WE NOW REPORT: -

### QUALITY: -

Sampling: - Carried out by our inspector, based on JIS M8100/1984 as indicative sampling, all the drawn samples were duly and thoroughly mixed up together forming an indicative sample that divided into (3) sub-samples, which sealed and labeled then distributed as follows:

Description	Seal Number(s)	Purpose
1 sealed sample	P8406895	Retained by SGS Egypt for 90 days unless written instructions received.
1 sealed sample	P8406894	Analysis at SGS Minerals Lab.
1 sealed sample	P8406897	Submitted to supplier.

Analysis: -On basis of the indicative sample drawn by SGS inspector, sealed with SGS seal no. P8406894, and prepared for analysis at SGS Mineral Lab. where the analysis results as follow: -

ioi alialysis al 303 ivillierai Lau	, where the analysis results as long	VV toprove
Test	Result %	Method
Moisture	0.23	
Purity (NaCl)	99.180	
Water Insoluble Matter	0.05	Ta.
SO <sub>4</sub>	0.42	
Ca	0.09	ASTM E534/2003
Mg takeday	0.08	12.0
CaSO <sub>4</sub>	0.31	3.5
MgSO <sub>4</sub>	0.25	
MgCl <sub>2</sub>	0.11	
Cu 48773	0.01	Atomic Absorption
*** <b>K</b> **	0.01	Spectrometry
Sieve Distribution (mm)	14 4 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	
+2.00		V analysis outside outside the direct visit of the displace follows
+1.70 - 2.00	22.68	ASTM E534/2003
+1.40 - 1.70	34.77	
-1.40		

Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months. Due to the inaccessibility of part of the cargo, the samples collected have indicative value only and will not necessarily be representative of the entire cargo, but only of that part accessible and sampled at the date, time, and place of inspection.

-- End of Report -----

Mineral Services: +(203) 5728810, 5728812, 5728833

Alexandria Office: 8 Fahmi Wissa St, Louran

**Head Office** 

: +(202) 27263000 : sgs\_egypt@sgs.com

E-mail Our Ref. NO.

: 2002255

Date

: 21st November 2017

Issuance

: Alexandria,

Report No.:190201/ Ore001295

Page: 1 of 1

## PRE-SHIPMENT REPORT

Pursuance of an order for inspection given to us by our principal "EGYPT SALT EXPORT"

Description of goods

: about 1100 MT salt 0.8mm to 1.4mm.

Place of Sampling

: Client Store, 10th of Ramadan city.

Date of Sampling

: 13.11.2017.

### WE NOW REPORT: -

#### QUALITY: -

Sampling: - Carried out by our inspector, based on JIS M8100/1984 as indicative sampling, all the drawn samples were duly and thoroughly mixed up together forming an indicative sample that divided into (3) sub-samples, which sealed and labeled then distributed as follows:

Description	Seal Number(s)	Purpose
1 sealed sample	P8406875	Retained by SGS Egypt for 90 days unless written instructions received.
1 sealed sample	P8406877	Analysis at SGS Minerals Lab.
1 sealed sample	P8406876	Submitted to supplier.

Analysis: -On basis of the indicative sample drawn by SGS inspector, sealed with SGS seal no. P8406877, and prepared for analysis at SGS Mineral Lab, where the analysis results as follow: -

Test	Result %	Method	
Moisture	0.25	12/2	
Purity (NaCl)	99.190		
Water Insoluble Matter	0.06		
SO <sub>4</sub>	0.36		
Ca	0.10	ASTM E534/2003	
Mg	0.07	1-7	
CaSO <sub>4</sub>	0.34	98.5	
MgSO <sub>4</sub>	0.15		
MgCl <sub>2</sub>	0.16		
Cu	0.01	Atomic Absorption	
K	0.01	Spectrometry	
Sieve Distribution (mm)	200 (A)		
+1.40	0.31		
+1.18 - 1.40	0.01	ASTM E534/2003	
+1.00 - 1.18	34.73	A3 IN E334/2003	
+0.850 - 1.00	29.65		
-0.850	35.30		

Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months. Due to the inaccessibility of part of the cargo, the samples collected have indicative value only and will not necessarily be representative of the entire cargo, but only of that part accessible and sampled at the date, time, and place of inspection.

---- End of Report -----

Mineral Services: +(203) 5728810, 5728812, 5728833

Alexandria Office: 8 Fahmi Wissa St, Louran

Head Office

: +(202) 27263000 : sgs\_egypt@sgs.com

E-mail Our Ref. NO.

: 2002255

Date

: 21st November 2017

Issuance

: Alexandria,

Report No.:190201/ Ore001296

Page: 1 of 1

## PRE-SHIPMENT REPORT

Pursuance of an order for inspection given to us by our principal "EGYPT SALT EXPORT"

Description of goods

: about 400 MT salt 0.30mm to 0.80mm.

Place of Sampling

: Client Store, 10th of Ramadan city.

Date of Sampling

: 13.11.2017.

### WE NOW REPORT: -

#### **QUALITY: -**

<u>Sampling:</u> Carried out by our inspector, based on JIS M8100/1984 as indicative sampling, all the drawn samples were duly and thoroughly mixed up together forming an indicative sample that divided into (3) sub-samples, which sealed and labeled then distributed as follows:

Description	Seal Number(s)	Purpose
1 sealed sample	P8406896	Retained by SGS Egypt for 90 days unless written instructions received.
1 sealed sample	P8406898	Analysis at SGS Minerals Lab.
1 sealed sample	P8406899	Submitted to supplier.

Analysis: -On basis of the indicative sample drawn by SGS inspector, sealed with SGS seal no. P8406898, and prepared for analysis at SGS Mineral Lab, where the analysis results as follow: -

Test	Result %	Method
Moisture	0.28	5 ~ 3
Purity (NaCl)	99.160	
Water Insoluble Matter	0.08	
SO <sub>4</sub>	0.33	
Ca	0.11	ASTM E534/2003
Mg sandaka	0.07	
CaSO <sub>4</sub>	0.37	
MgSO <sub>4</sub>	0.08	
MgCl₂ ******	0.21	
Cu Marian	0.01	Atomic Absorption
**************************************	0.01	Spectrometry
Sieve Distribution (mm)	1000 ** ** ** ** ** ** ** ** ** ** ** **	
+0.850 0.57		
+0.600 - 0.850	21.25	ASTM E534/2003
+0.500 - 0.600	21.90	
+0.300 - 0.500	47.90	
-0.300	8.38	

Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months.

Due to the inaccessibility of part of the cargo, the samples collected have indicative value only and will not necessarily be representative of the entire cargo, but only of that part accessible and sampled at the date, time, and place of inspection.

10. and place of inspection.