# TEST CERTIFICATE

**EN 10204 : 2004 TYPE 2.2**

EMG

EMG

[redacted]

CUSTOMER: BPM Trade SRL
P.O/INVOICE NO.: 38-10-0001
P.O/INVOICE DATE: 25.11.2022
DIMENSIONS , mm
**STEEL GRADE & SPECIFICATION: S235JR DIN EN 10051**
TYPE OF PRODUCT, DESCRIPTION: HOT ROLLED STEEL SHEETS/PLATES

DATE: 27.10.2022
REPORT NO: 1432

| HEAT NO | AMOUNT (KG) | Grade | DIMENSION (MM) | P.S. or P.P. | MECHANICAL PROPERTIES: TENSILE TEST: SAM POS. | YIELD STRENGTH | TENSILE STRENGTH | % EL | BEND TEST | BH VAL. | VAL. APPL. (Joules) | CVN (Joules) | HARDNESS | IMPACT TEST (joule) POSITION: 1 | 2 | 3 | AV | NP % | HEAT TEMP. YIELD N/MM² | CHEMICAL COMPOSITION (TOTAL ANALYSIS): C % | MN % | P % | S % | SI % | Cr |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 31096762-03 | | S235JR | 14x1500x6000 | | | 301 | 409 | 31,5 | OK | | | | | | | | | | | 0,126 | 0,444 | 0,012 | 0,016 | 0,030 | 0,031 |
| 31072319-02 | | S235JR | 14x1500x6000 | | | 301 | 409 | 31,5 | OK | | | | | | | | | | | 0,126 | 0,433 | 0,012 | 0,009 | 0,030 | 0,030 |
| 31073854-02 | | S235JR | 16x1500x6000 | | | 286 | 394 | 31,5 | OK | | | | | | | | | | | 0,126 | 0,433 | 0,014 | 0,009 | 0,028 | 0,030 |

WE THE SUPPLIER, HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MADE BY THE BASIC OXYGEN PROCESS AND TESTED IN ACCORDANCE WITH THE RULES OF DIN EN 10204 AND THE DATA GIVEN ARE A TRUE AND CORRECT RECORD OF THE RESULTS OBTAINED.

SIGNED

NOTE: T.E., M. Middle, E. End, T. Transverse, L. Longitudinal, P.S. Piece Sample, P.P. Piece of Plate

Digitally signed by Zuev Alexei
Date: 2026.05.04 11:21:10 EEST
Reason: MoldSign Signature
Location: Moldova
MOLDOVA EUROPEANĂ