



Technical Data Sheet

| Parameters | Standard | Unit | Measurement |
|------------------|------------|------------------|-------------|
| Substance | ISO 536 | g/m ² | 80 |
| Thickness | ISO 534 | µm | 106 |
| Bulk | ISO 534 | | 1,33 |
| Moisture content | ISO 287 | % | 4,1 |
| Roughness | ISO 8791 | Bendtsen ml/min | 220 |
| Whiteness | ISO 11475 | CIE | 150 |
| Brightness | ISO 2470-2 | % | 107 |
| Opacity | ISO 2471 | % | 91 |



References:

Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp

Sylvamo Sweden AB
Nymöllavägen 260-15, 295 73
Nymölla, Sweden
Extract date: May 2023