## Изпитвателен център ГЛОБАЛТЕСТ

1618 София, ул. "Крушовски връх" № 31 . Тел./факс 0700 20 661 www.globaltest-bg.com office@globaltest-bg.com



## **Testing Center GLOBALTEST**

Bulgaria, 1618 Sofia, 31 Krushovski vrah Str. Tel/fax +359 700 20 661 www.globaltest-bg.com office@globaltest-bg.com

## TEST REPORT

Nº and date of test report RN43687 / 24/07/2023

Internal request for testing №

RN43687 / 30/05/2023

Testing period

23/06/2023-20/07/2023

Customer: **ORGACHIM JSC** 

Customer's address: 21 Treti mart blvd., Ruse, Republic of Bulgaria

№ and date of assignment document: Application for testing by Katerina Petrova from 30/05/2023

Method of arrival of the test item: Courier delivery by "Speedy" via waybill

1000621816342891420001963019

Date of receipt of test item: 30/05/2023

Test item: Type: WB primer, category: arch, Product name: DEKO G8400

Contact grund, VOC Category: A/g 30g/l, Lot: lab sample

Manufacturer: **ORGACHIM JSC** 

Normative references: BDS EN ISO 11890-2:2020

Number of test items: 200g

M Chem Ivan Givechev Test performed by:

ория ГЛО

**Dimitar Tanev** Test report issued by:

TC GLOBALTEST Manager Dipl.eng.Dimitar Tanev

signature

Results are listed on pages 2 to 2

ESD 7.8-2

NOTE:

stamp

Test results are only for the tested item. The report could be used only in its whole. Test report is valid only with "wet" stamp or signed electronically.

## RESULTS FROM TESTS - Test report RN43687 / 24/07/2023

Type of characteristic / Parameter	Method	Unit of measurement	Limit (Range)	Result	Uncertainty	Test conditions
Volatile organic compounds (VOC)	BDS EN ISO 11890-2:2020	%	Not specified	1.38*	-	T - 20.9°C; RH - 56%

<sup>\*</sup>Volatile organic compounds (VOC) content, in g/l: 15.18 (density of the product: 1.10 g/ml)

(a) – the test method is in scope of accreditation; (na) – the test method is out of scope of accreditation;