

Technical Data Sheet

HP Copy

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80 +/- 2
Thickness	ISO 534	µm	106 +/- 3
Bulk	ISO 534		1,33
Moisture Content	ISO 287	%	4,4 +/- 0,6
Roughness	ISO 8791-2	Bendtsen ml/min	220 +/- 50
Whiteness	ISO 11475	CIE	146 +/- 3
Brightness D65	ISO 2470-2	%	105 +/- 1
Opacity	ISO 2471	%	92 +/- 2
Stiffness MD	ISO 2493	mN	115 +/- 15
Stiffness CD	ISO 2493	mN	45 +/- 15

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety