



Emerald Photo Copy Paper

云豹 静电复印纸

ZJCM



## TECHNICAL SPECIFICATIONS

Items	项目	Unit	Standard/ Method	Parameters	
Basis Weight	定量	gsm	ISO 536	70	80
Caliper	厚度	µm	ISO 534	96±1	105±1
ISO Brightness	亮度	%	ISO 2470-1	96	96
Bulk	松厚度	cm <sup>3</sup> /g	ISO 534	1.37	1.31
Opacity	不透明度	%	ISO 2471	≥90	≥92
Stiffness	挺度	mN.m		≥0.30/0.10	≥0.40/0.13
Whiteness	视觉白度	%	CIE	≥148	≥148
Moisture	水分	%	ISO 287	5.0-5.5	5.0-5.5
Cobb	表面吸收重量	gsm	ISO 535	≤35	≤35
Smoothness	平滑度	s	ISO 5627	≥18	≥18
Folding Endurance	耐折度	times	ISO 5626	≥8	≥8

\* Test conditions: ISO Temperature: 23±1°C ; Humidity: 50±2%RH

\* Zhanjiang Mill is certified by ISO 9001, ISO 14001 & FSC

\* FSC grade is available

\* End uses: Photocopy, fax & laser printing, one side & two side color printing, ideal for office multi-purpose

\* ColorLok® enables faster drying, vivid colours and deep blacks

\* Cutsite available in 5 reams/carton & 10 reams/carton

