



STANDARD
100

BEWO 084394
TESTEX

This certificate BEWO 084394 is valid until
15.08.2026.

SUPPORTING DOCUMENTS

- ✓ Test report : BJ015 266840.1
- ✓ Declaration of conformity in accordance with
EN ISO 17050-1 as required by OEKO-TEX®
- ✓ OEKO-TEX® Terms of Use (ToU)

Matz Bachmann
Managing Director

Janine Kuchelmeister
Ecology Team Leader




Zurich, 2025-07-24

Mars-285

100% COTTON

285 GSM / TWILL 3/1



Fabric name	Mars - 285
Fabric weight	285 ± 5 gsm
Composition	100% Cotton
Full width	150 ± 2 cm
Weave	Twill 3/1
Finishes	-
Area of use	workwear
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1000	500
2	Tearing strength, N	ISO 13937-3:2000	30	28
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	30 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	3-4	
	Colour staining	ISO 105-C06:2010	N/A	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		3-4	
	Colour staining		3-4	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		3-4	
	Wet		2-3	
9	Colour Fastness To Light	ISO 105-B02:2013	N/A	

* The values shown are indicative and may vary slightly from batch to batch.

* N/A - not applicable.

www.xmtextiles.com