

Technical Data Sheet

HP Copy

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80
Thickness	ISO 534	µm	106
Bulk	ISO 534		1,33
Moisture Content	ISO 287	%	4,1
Roughness	ISO 8791	Bendtsen ml/min	240
Whiteness	ISO 11475	CIE	147
Brightness D65	ISO 2470-2	%	106
Opacity	ISO 2471	%	93

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety
ISO 50001 - Energy