

Mechanic-280

100% COTTON 280 GSM / TWILL 3/1



Fabric name	Mechanic-280
Fabric weight	280 ± 5 gsm
Composition	100% Cotton
Full width	150 ± 2 cm
Weave	twill 3/1
Finishes	_
Area of use	multi seasonal workwear
Washing instruction	₩ M D A P

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1000	500
2	Tearing strength, N	ISO 13937-3:2000	30	28
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 30 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3	-4
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	3	-4
	Colour staining	ISO 105-C06:2010	3	-4
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		3	-4
	Colour staining		3	-4
8	Colour Fastness To Rubbing, min. ISO 105-X12:2001			
	Dry		3	-4
	Wet		2	-3
9	Colour Fastness To Light	ISO 105-B02:2013	>	4

^{*} The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES ITALIA SRL



Test Report

SL52035273876801TX

Date:July 27,2020

Page 1 of 3

SHANGHIA XM GROUP LTD

ROOM 2403, ZHONGYI INTERNATIONAL BUILDING NO.1833, NORTH ZHONGSHAN ROAD, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric (MECHANIC-280,100% cotton, 280 gsm 150 cm,

Order:XMT-20-079)

Sample Color : (A)Dark Navy #21

Proposed Care Instruction:

Sample Receiving Date : Jul 22, 2020

Testing Period : Jul 22, 2020 - Jul 27, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Hattie Chen (Account Executive)

lattice Chen



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its Intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com



Test Report Test Result

SL52035273876801TX

Page 2 of 3

Colour Fastness To Light

(ISO 105-B02:2014; Method 2 (Modified), use Xenon arc lamp, Exposure Cycle: A1, no flip-flop mode was used)

Date:July 27,2020

Comparison upto blue wool reference 4

-	Unit	(A)
Grade(B.W.S)	-	4

Colour Fastness To Rubbing

(ISO 105-X12:2016; Size of rubbing finger: 16mm dia.)

As Received

-	Unit	(A)
Dry Staining	-	4-5
Wet Staining	-	3

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Colour Fastness To Washing

(ISO 105-C06:2010; Test No.:C2S, Machine wash at 60℃ with 4g/L ECE (B) and 1g/L Sodium Perborate with 25 Steel Balls)

-	Unit	(A)
Change in Shade	-	4-5
Staining On Multi-fibre Stripe		
Acetate	-	4-5
Cotton	-	4-5
Polyamide	-	4-5
Polyester	-	4-5
Acrylic	-	4-5
Wool	-	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its Intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3stBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国 • 上海 • 徐江区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86–21) 64958763 f (86–21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report

SL52035273876801TX

Date:July 27,2020

Page 3 of 3

Dimensional Stability To Washing

(ISO 3759:2011/ISO 5077:2007/ISO 6330:2012; Using horizontal axis, front-loading type machine; Procedure No.6N, Machine Wash At 60℃; with 2kg total dry mas s (Type I (100% Cotton) Ballast+ Specimen), 'ECE(A)' detergent+ Sodium Perborate+ TAED, Tumble Dry Low, Less Than 60℃, warm iron)

After 1 Wash

-	Unit	(A)
Lengthwise	%	-3.0
Widthwise	%	-0.4

Remark: (+)Means Growth; (-)Means Shrinkage

Tearing Strength

(ISO 13937-2:2000;)

-	Unit	(A)
Warp/Length Yarns Torn	N	33
Weft/Width Yarns Torn	N	37

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666

f (86-21) 64958763

www.sgsgroup.com.cn e sgs.china@sgs.com



This certificate BEWO 084394 is valid until 15.08.2025.

SUPPORTING DOCUMENTS

- ✓ Test report: BJ015 245163.1
- Declaration of conformity in accordance with EN ISO 17050-1 as required by OEKO-TEX*

dimin

✓ OEKO-TEX® Terms of Use (ToU)

Matz Bachmann

Managing Director

Dijana Ajdilovic

Ecology Team Leader