

TECHNICAL DATA SHEET

STERILIZATION FLAT/GUSSET REEL, 60gsm

PK	ODUCT CODE	:	4AFR (Flat l	Reel) - 4AGR (Gusset Reel)		
REI	RELATED STANDARDS		4A Medical flat and gusseted reels are manufactured according to EN 868-5 and ISO 11607 standards. The indicator used in the reel production is classified as Class 1 Type Indicator according to the ISO 11140-1 standard. 4A Medical Reels meet the requirements of 93/42/EEC Medical Device Directive regulations			
INT	INTENDED USE		4A Medical reels are designed to provide excellent barrier for sterile medical device packaging purposes. Reels meet the Medical Industry's requirement for high quality, hygiene and safety levels. 4A Medical reels are used for the packing of the Medical Devices before sterilization and it maintains the sterility of the products after sterilization. 4A Medical reels are ease to package and indicator used for the sterilization provides information with the sterilization status of the medical devices. Sterilized material in sterilization package is storable for up to 5 years after the sterilization in a clean room conditions.			
FIL	FILLING VOLUME		According to DIN 58953-7 (German national standard): Seleable paper bags and seleable pouches and reals shall be filled up to 3/4 max of their volume. This limits avoids too high stress / burdon to the seals. Belowe the buttom seal there must be space of minimum 30 mm between load and sealing area. There is no known limit bu standarts for weight and it is based on experience. However, it is suggested to follow the 3/4 rule. In terms of solid, heavy load (metal instruments), it is the weight itself, in case of any sharp objects which could demage the material, and the volume of condensate (directly related to mass=weight) which is created during the steam sterilization.			
OPI	OPERATION CONDITIONS		4A Medical reels are used for steam, ethylene oxide, formaldehyde sterilization methods. The sterilization conditions should be determined by the end user regarding to material to be sterilized.			
SPE	ECIFICATIONS	:				
	PROPERT					
	PROPERT	TIES		UNITS	STANDARD	TYPICAL VALU
	PROPERT SUBSTANCE	TIES		UNITS g/m²	STANDARD ISO 536	TYPICAL VALU
		TIES				
	SUBSTANCE	TIES		g/m²	ISO 536	60,0
	SUBSTANCE THICKNESS	TIES		g/m² μm	ISO 536 ISO 534	60,0
	SUBSTANCE THICKNESS BENDTSEN POROSITY			g/m² μm ml/min	ISO 536 ISO 534 ISO 5636-3	60,0 76 650
	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE	FS		g/m² μm ml/min μm (Pa*s)	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3	60,0 76 650 7,4
8	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS	FS		g/m² μm ml/min μm (Pa*s) ml/min	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2	60,0 76 650 7,4 250
APER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS I BENDTSEN ROUGHNESS I	FS		g/m² µm ml/min µm (Pa*s) ml/min ml/min	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2	60,0 76 650 7,4 250 250
AL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS TO BENDTSEN ROUGHNESS TO PORE SIZE	FS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D)	60,0 76 650 7,4 250 250 17
OICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS OF THE STRENGTH, MD	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm (kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2	60,0 76 650 7,4 250 250 17 5,9
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS SENDTSEN ROUGHNESS SENDTSEN ROUGHNESS SENDTSEN SIZE TENSILE STRENGTH, MD TENSILE STRENGTH, CD	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 1924-2	60,0 76 650 7,4 250 250 17 5,9 2,9
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS OF THE STRENGTH, MD TENSILE STRENGTH, MD WET TENSILE STRENGTH	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS I BENDTSEN ROUGHNESS I PORE SIZE TENSILE STRENGTH, MD TENSILE STRENGTH, CD WET TENSILE STRENGTH WET TENSILE STRENGTH	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm kN/m kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781 ISO 3781	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6 0,9
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS OF THE STANDARD STANDA	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm kN/m kN/m kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781 ISO 3781 ISO 2758	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6 0,9 300
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS I BENDTSEN ROUGHNESS I PORE SIZE TENSILE STRENGTH, MD TENSILE STRENGTH, CD WET TENSILE STRENGTH WET TENSILE STRENGTH BURST STRENGHT WET BURST	FS WS		g/m² µm ml/min µm (Pa*s) ml/min µm kN/m kN/m kN/m kN/m kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781 ISO 3781 ISO 2758 ISO 3689	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6 0,9 300 100
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS OF THE STAND THE STRENGTH, MD TENSILE STRENGTH, CD WET TENSILE STRENGTH WET TENSILE STRENGTH BURST STRENGTT WET BURST TEARING STRENGHT MD	FS WS		g/m² µm ml/min µm (Pa*s) ml/min ml/min µm kN/m kN/m kN/m kN/m kN/m kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781 ISO 3781 ISO 2758 ISO 3689 ISO 1974	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6 0,9 300 100 600
MEDICAL PAPER	SUBSTANCE THICKNESS BENDTSEN POROSITY AIR PERMEANCE BENDTSEN ROUGHNESS I BENDTSEN ROUGHNESS I PORE SIZE TENSILE STRENGTH, MD TENSILE STRENGTH, CD WET TENSILE STRENGTH WET TENSILE STRENGTH WET TENSILE STRENGTH WET BURST TEARING STRENGHT MD TEARING STRENGHT CD	FS WS		g/m² µm ml/min µm (Pa*s) ml/min µm kN/m kN/m	ISO 536 ISO 534 ISO 5636-3 ISO 5636-3 ISO 8791-2 ISO 8791-2 EN 868-2 (app.D) EN ISO 1924-2 EN ISO 3781 ISO 3781 ISO 2758 ISO 3689 ISO 1974 ISO 1974	60,0 76 650 7,4 250 250 17 5,9 2,9 1,6 0,9 300 100 600 650



TECHNICAL DATA SHEET

STERILIZATION FLAT/GUSSET REEL, 60gsm

UNIT	TYPICAL VALUE	
	LAM.FILM	52 ± 5
Micron	PE	40 ± 5
	PET	12 ± 2
N/15mm	35	
mN	300	
N/m	265	
%	70	
min/degrees	30 min/140C	
	N/15mm mN N/m	Micron PE PET PET N/15mm 35 mN 300 N/m 265 % 70

PRODUCT SPECIFICATION

	PROPERTIES	UNIT	TYPICAL VALUE
РОИСН	SEAL STRENGTH	N/15mm	2,5
	BUBBLE TEST		None
	PINHOLE DETERMINATION		None
	DIMENSION CONTROL	cm or mm	Desired dimensions
	LEAKAGE TEST		None
	PEEL DIRECTION		None
	INDICATOR CONTROL		Returns the specified color

INDICATOR	STERILIZATION METHOD	BEFORE STERILIZATION	AFTER STERILIZATION
	STEAM	BLUE	GREEN
	EO	PINK	ORANGE
	FORMALDEHYDE	PURPLE	GREEN
		4A Medical reels are packaged in carton boxes as below: Flat Reels are 200m long and Gusset Reels are 100m long.	

Product dimensions	Pieces in carton
50mm X 200m /	10
75mm X 200m / 75mm X 100m	8
100mm X 200m / 100mm X 100m	8
120mm X 200m / 120mm X 100m	4
150mm X 200m / 150mm X 100m	4
200mm X 200m / 200mm X 100m	4
250mm X 200m / 250mm X 100m	2
300mm X 200m / 300mm X 100m	2
350mm X 200m / 350mm X 100m	2
400mm X 200m / 400mm X 100m	2
420mm X 200m / 420mm X 100m	2
450mm X 200m / 450mm X 100m	2
500mm X 200m /500mm X 100m	2

MANIFACTURER