

Technical Data Sheet

HP Earth First

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80 +/- 2
Thickness	ISO 534	µm	108 +/- 3
Bulk	ISO 534		1,35
Moisture Content	ISO 287	%	4,4 +/- 0,6
Roughness	ISO 8791-2	Bendtsen ml/min	230 +/- 50
Whiteness	ISO 11475	CIE	161 +/- 3
Brightness D65	ISO 2470-2	%	109,5 +/- 1
Opacity	ISO 2471	%	92 +/- 2
Stiffness MD	ISO 2493	mN	130 +/- 15
Stiffness CD	ISO 2493	mN	50 +/- 15

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:

Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety