

Tel +44 1942 265 700 consumergoods.uk@intertek.com intertek.com



FLAMMABILITY TEST REPORT

Report No.: LEI18105149A Date Received: 29/10/18 **Date Tested:** 02/11/18 **Date Issued:** 02/11/18

SC VITAFOAM ROMANIA SRL **Company Name & Address:**

STR. 1 MAI, NR. 34

LUDUS JUD, MURES **ROMANIA** COD: 545200

Contact Name: GEORGE BARBET

Sample Details

Reference No.: 0001.15.10.18VFR Order No.: 01/15.10.2018

Style No.: Combustion modified polyurethane foam, made from: polyol, TDI and flame

retardants, density 30kg/m³, hardness 148N

Batch No .: P225, produced 12 Oct 2018 from short blocks, randomly taken in 15 Oct 2018

Quality: CM3037 White Colour:

Vitafoam Romania SRL Supplier:

End Use: Not stated Quoted Fibre Composition: Not stated Retailer: Not stated

Sample Description: White coloured polyurethane foam

| Test Method | Pre Treatment | Flammability Performance Requirements | Result |
|---|---------------|--|----------|
| BS 5852: Part 2: 1982, Ignition source 5 (Crib 5) as modified by Schedule 1 Part 1 of the Furniture & Furnishings (Fire) (Safety) Regulations 1988 (As Amended). | None | As Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). | Complies |

STEVEN OWEN (Technical & Operational Excellence Manager)

ANDREW HALLETT (Flammability Team Leader)

CAROLE SPOWART (Flammability Administrator)

GREGORY JAMES (Flammability Technician)

Report No.: LEI18105149A Page 1 of 2













Intertek The Warehouse Brewery Lane Leigh WN7 2RJ UK

FLAMMABILITY TEST REPORT

Filling Specification

Filling Type: Polyurethane foam Density / Hardness: 30k/g/m³ / 148N

Cover Fabric: Standard test fabric as detailed in Schedule 1 Part 1 of The Furniture (Fire) (Safety)

Regulations 1988 (as amended).

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere

having a temperature of 20±5°C and a relative humidity of 50±20%

At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 70%

Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the fully potential fire hazard of the materials in use."

| Pass / Fail Criteria | Initial test | | Repeat test | |
|--|---|-----|---|-----|
| Progressive smouldering failure | | | | |
| Externally detectable amounts of smoke, heat or glowing 60 min after crib ignition | No | | No | |
| Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction | No | | No | |
| Smouldering essentially consumed the test specimen within the duration of the test | No | | No | |
| Flaming failure | | | | |
| The test specimen continued to flame for more than 10 minutes after the ignition of the crib | No | | No | |
| Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction | No | | No | |
| Flaming essentially consumed the test specimen within the duration of the test | No | | No | |
| Final examination | | | | |
| Progressive smouldering was observed when the sample was dismantled | No | | No | |
| Comments | | | | |
| Time to extinction of flames after crib ignition | 3 Minutes 09 Seconds | | 2 Minutes 37 Seconds | |
| Time to extinction of glowing after crib ignition | Due to the position of the crib within the test specimen it was not possible to see when glowing ceased | | Due to the position of the crib within the test specimen it was not possible to see when glowing ceased | |
| Time to extinction of smoke after crib ignition | Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased | | Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased | |
| Maximum extent of damage to back (mm) Length / Width | 400 | 143 | 400 | 135 |
| Maximum extent of damage to base (mm) Length / Width | 120 | 173 | 115 | 147 |
| The resultant mass loss exceeded 60g | No (29g) | | No (27g) | |
| Test Result | PASS | | PASS | |

Conclusions

The sample tested meets the requirements of Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have <u>aimed</u> to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Report No.: LEI18105149A Page 2 of 2







