

LAMINATED SPUNBOND FABRIC TECHNICAL DATA SHEET



TOTAL WEIGHT : **60** GSM
MATERIAL STRUCTURE : 35 GSM SPUNBOND + 2 GSM HOTMELT+ 23 GSM PE EXTRUSION FILM
PRODUCT NAME : LAMINATED SPUNBOND (ANTISTATIC)+PE BREATHABLE FILM HOTMELT_

CHARACTERISTIC	UNIT	TARGET VALUE	MIN. VALUE	MAX. VALUE	TEST METHOD
TENSILE STRENGTH (MD)	N / 5 cm	130,0	120,0	140,0	NWSP 110.4.R0 (15)
TENSILE STRENGTH (CD)	N / 5 cm	65,0	55,0	75,0	NWSP 110.4.R0 (15)
ELONGATION (MD)	%	40,0	30,0	50,0	NWSP 110.4.R0 (15)
ELONGATION (CD)	%	75,0	65,0	85,0	NWSP 110.4.R0 (15)
HYDROSTATIC PRESSURE	mmH ₂ O	3200	2500	3600	NWSP 080.6.R0 (15)

- ✓ **EN ISO 10993-5** Cytotoxicity= After 24 hours, no biological reactivity
Report No : B.30.2.HAC.0.03.00.00 (Hacettepe University)
- ✓ **EN ISO 10993-10** Skin irritation = Does not cause skin irritation
Report No : B.30.2.HAC.0.03.00.00 (Hacettepe University)
- ✓ **OEKO-TEX STANDART 100** Certificate Number 09.HTR.73667



Y.F.S. SIDA TEM. AMBALAJ
MEDİKAL TEKSTİL SAN. TİC. LTD. ŞTİ.
 Tel : 0312 291 85 00 0312 291 85 05
 E-mail: info@yfs.com.tr yfs@yfs.com.tr
 Caddesi: 15. Yıl San. Bölgesi 06100 ANKARA