

## 2K-Deripox Protec ZP

Rapid drying two component zinkphosphate primer on epoxy resin basis, chemical cured with polyamine adduct. Free of lead, cadmium and chromium VI compounds

### Field of application

- Protection against corrosion for iron steel and galvanized steel.
- Coating system with 2K-Derocryl Lack 70 ST certified for corrosion protection category C5 high (ILF 200417).
- It is possible to spray 3 layers a day.
- Using even at low temperatures.

### Product properties

- High Solid
- Resistance to chemicals (on request)
- Resistance to mineral oils
- High surface hardness
- Fast drying
- Fast recoatability
- Recoatability: with two component topcoats

### Technical Specification

Colours	<b>redbrown</b> , light-grey, grey. Other colours upon request.
Flash point	>23 °C
Temperature stability	-40 up to 200 °C
Gloss	Silky mat
Potential dry film thickness in one working process	80 up to 160 µm
Mixing ratio	<b>Hardener HL 560</b>
(Basis:hardener) by weight	9:1
(Basis:hardener) by volume	4,7:1
Pot life in hours	2
Viscosity	Thixotrope
Density in kg/l	1,6
Solid content in %	82
Solid volume in %	66
Theoretical spreading capacity	<ul style="list-style-type: none"> <li>• 8,25 m<sup>2</sup>/l at 80 µm DFT</li> <li>• 5,16 m<sup>2</sup>/kg at 80 µm DFT</li> </ul>
Recommended film thickness	125 µm WFT corresponds to 80 µm DFT
Drying (DIN EN ISO 1517)	80 µm DFT
Dust-dry (Tg1)	After 30 min
Touch-dry (Tg4)	After 2 h
Dry (Tg6)	After 3 h
Cured chemically	After 7 days
Interval for overcoating	<ul style="list-style-type: none"> <li>• after 3 h with two component topcoats</li> </ul>
Note	<ul style="list-style-type: none"> <li>• The specifications are related to the prepared mixture and are based on standard atmospheric conditions 23/50, DIN 50014.</li> <li>• Lower temperatures and/or higher humidity will prolong drying and hardening.</li> <li>• It is possible to use this material to limit frost temperature (possibly solvents are necessary).</li> </ul>

**Safety information** (See Security Data Sheet)

## 2K-Deripox Protec ZP

VOC-level	Appr. 299 g/l
Solvent content	Appr. 19 % by weight
Aromatic content	Appr. 12 % by weight

### Storage

Storage	<ul style="list-style-type: none"> <li>In dry, cool rooms, if possible frost-proof</li> <li>Ensure good ventilation</li> </ul>
Shelf life	<ul style="list-style-type: none"> <li>6 month from date of delivery when in unopened original containers in cool and dry conditions</li> </ul>

### Application methods

Mixing ratio	<ul style="list-style-type: none"> <li>Stirr homogeneous, preferably with mechanical stirrer</li> <li>Mix base paint and hardener according to the mixing ratio as specified</li> </ul>
Airless spraying	<ul style="list-style-type: none"> <li>Flow pressure 180 bar</li> <li>Nozzle size 0,015 - 0,019 inch (0,38 - 0,48 mm)</li> <li>Spraying angle according to the geometry and size of the object to be laquered</li> </ul>
Compressed air spraying	<ul style="list-style-type: none"> <li>Spraying pressure 5 - 6 bar</li> <li>Nozzle size 1,6 - 1,8 mm</li> <li>Adjust to spraying viscosity (appr. 60 s DIN 4 mm) adding appr. 10 % Deripox-Verdünnung (two component products: after mixing)</li> </ul>
Electrostatic application	<ul style="list-style-type: none"> <li>Application is possible provided that the material is diluted</li> </ul>
Dipping	<ul style="list-style-type: none"> <li>Can not be applied as delivered</li> </ul>
Other methods	<ul style="list-style-type: none"> <li>Roller and brush application is possible in the quality as delivered</li> </ul>
Thinner	<ul style="list-style-type: none"> <li>Max. 10% Deripox-Verdünnung</li> </ul>
Cleaning	<ul style="list-style-type: none"> <li>Rinse immediately with Deripox-Verdünnung</li> </ul>
<b>Preparation of support</b>	<ul style="list-style-type: none"> <li>Shot blasting to a purity according to SA 2½</li> <li>Sweeping for zincd supports</li> <li>Mill scale, welding residues, dust and dirt on the surface which might reduce adhesion have to be carefully and thoroughly removed</li> </ul>
<b>General remarks</b>	<ul style="list-style-type: none"> <li>During coating and drying the humidity should be min. 30 % / max. 85 %</li> <li>During coating and drying the environmental temperature should be min. 5°C / max. 30°C</li> <li>Object temperature at least 3° C above dew point.</li> </ul>
<b>Example for a system</b>	<ul style="list-style-type: none"> <li>Primer coat: 2K-Deripox Protec ZN</li> <li>Intermediate coat: 2K-Deripox Protec ZP</li> <li>Finish coat: 2K-Derocryl Lack 80 HS</li> </ul>

*The general information and descriptions contained in this specification are provided to the best of our knowledge. Our information and specifications do not constitute warranted characteristics in the legal sense. Any advice for preparation and application which may be provided verbally, in writing or by means of experiments is of general nature only, and any property rights of third parties are also to be regarded in this context. Our general instructions do not release you from your obligation to check the suitability of the products supplied by our company for the intended methods and purposes of application. Particular in those cases when our supplied material will be applied with products from other sources. The products are prepared, applied and used outside of our sphere of control and thus fall solely within the user's scope of responsibility.*

*Our general terms of sale and delivery apply as agreed.*

Product group: EG4002351000