

1K DC Lack Hydro Color

Water borne coating on an acrylat dispersion binder with an activ anti-corrosive pigment

Field of application	<ul style="list-style-type: none"> • Protection against corrosion for steel constructions and cast iron. • Using as one layer or top coat. • Complies with ChemVOCFarb V section 1d metal coatings. • Category 16 and 19 of DGnB quality level 1-4.
Product properties	<ul style="list-style-type: none"> • Medium Solid • Water based • Contains zincphosphate • Resistance to mineral oils • Fast drying
Technical Specification	
Colours	RAL 5012 , RAL-colour chart, apart from RAL 9006/9007.
Flash point	Not applicable
Temperature stability	-20 up to 150 °C
Gloss	Mat
Potential dry film thickness in one working process	60 up to 80 µm
Viscosity	Thixotrope
Density in kg/l	1,37
Solid content in %	62
Solid volume in %	46
Theoretical spreading capacity	<ul style="list-style-type: none"> • 5,75 m²/l at 80 µm DFT • 4,2 m²/kg at 80 µm DFT
Recommended film thickness	175 µm WFT corresponds to 80 µm DFT
Drying (DIN EN ISO 1517)	80 µm DFT
Dust-dry (Tg1)	After 25 min
Touch-dry (Tg4)	After 40 min
Dry (Tg6)	After 3 h
Accelerated drying	30 min. at 60°C possible, after 10 min. flash-off time
Interval for overcoating	<ul style="list-style-type: none"> • after 1 h with itself
Note	<ul style="list-style-type: none"> • The specifications are based on standard atmospheric conditions 23/50, DIN 50014. • Lower temperatures and/or higher humidity will prolong drying and hardening.
Safety information (See Security Data Sheet)	
VOC-level	Appr. 53 g/l
Solvent content	Appr. 4 % by weight
Aromatic content	Appr. 3 % by weight
Storage	
Storage	<ul style="list-style-type: none"> • In dry, cool rooms, frost-proof • Ensure good ventilation
Shelf life	<ul style="list-style-type: none"> • 6 month from date of delivery when in unopened original containers in cool and dry conditions
Application methods	

1K DC Lack Hydro Color

Airless spraying	<ul style="list-style-type: none"> • Risk of spray dust due to very fast drying • After using the material close the packings immediately • Dip the pistol and the nozzle into water during the breaks • It is tending to fast skinning. Do not stir the skin in any case! • Flow pressure 120 - 180 bar • Nozzle size 0,011 - 0,013 inch (0,28 - 0,33 mm)
Compressed air spraying	<ul style="list-style-type: none"> • Spraying pressure 4 bar • Nozzle size 1,3 - 1,5 mm • Adjust to spraying viscosity (appr. 30 s DIN 4 mm) adding appr. 5 % Water (two component products: after mixing)
Electrostatic application	<ul style="list-style-type: none"> • Application is possible, provided the equipment is suitable for water based materials
Dipping	<ul style="list-style-type: none"> • Can not be applied as delivered
Other methods	<ul style="list-style-type: none"> • Roller and brush application for repair work is possible
Thinner	<ul style="list-style-type: none"> • Max. 8% Water
Cleaning	<ul style="list-style-type: none"> • Rinse immediately with Wasser • Residues are dissolvable with Deripox-Verdünnung
Preparation of support	<ul style="list-style-type: none"> • Shot blasting to a purity according to SA 2½ • If necessary clean with high pressure-cleaner and turbo-cleaner-solution • Mill scale, welding residues, dust and dirt on the surface which might reduce adhesion have to be carefully and thoroughly removed
General remarks	<ul style="list-style-type: none"> • During coating and drying the humidity should be min. 30 % / max. 85 % • During coating and drying the environmental temperature should be min. 5°C / max. 30°C • Object temperature at least 3° C above dew point.
Example for a system	<ul style="list-style-type: none"> • Primer coat: Derocryl Grund Hydro GT • Finish coat: 1K DC Lack Hydro Color

The general information and descriptions contained in this specification are provided to the best of our knowledge. Our information and specifications do not constitute warranted characteristics in the legal sense. Any advice for preparation and application which may be provided verbally, in writing or by means of experiments is of general nature only, and any property rights of third parties are also to be regarded in this context. Our general instructions do not release you from your obligation to check the suitability of the products supplied by our company for the intended methods and purposes of application. Particular in those cases when our supplied material will be applied with products from other sources. The products are prepared, applied and used outside of our sphere of control and thus fall solely within the user's scope of responsibility.

Our general terms of sale and delivery apply as agreed.

Product group: AD7012