



Fabric name	Prima-160 Stretch
Fabric weight	160 ± 5 gsm
Composition	53% Cotton, 44% Polyester, 3% Spandex
Full width	150 ± 2 cm
Weave	twill 2/1
Finishes	Peach
Area of use	HoReCa uniform
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1100	310
2	Tearing strength, N	ISO 13937-3:2000	25	21
3	Dimensional Stability To Washing 60°C, max	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
5	Pilling Resistance after 7000 revol.	ISO 12945-2:2000	4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010	4-5	
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining to cotton	ISO 105-C06:2010	4-5	
	Colour staining to polyester	ISO 105-C06:2010	4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		2	
9	Colour Fastness To Light	ISO 105-B02:2013	4	

* The values shown are indicative and may vary slightly from batch to batch.

