

iQ TORO SC technical data

CERTIFICATION & CLASSIFICATION	STANDARDS	iQ Toro SC
Type of floor covering	ISO 10581	Permanently static conductive pressed homogeneous vinyl flooring
Binder content	ISO 10581	Type I
CE certification	EN 14041	Yes
Classification	ISO 10874	Commercial: 34 Industrial: 43


TECHNICAL CHARACTERISTICS	STANDARDS	iQ Toro SC
Wear layer thickness	ISO 24340	2.0 mm
iQ PUR		Yes
Total thickness	ISO 24346	2.0 mm
Total weight/m ²	ISO 23997	2950 g
Form of delivery	ISO 24341	Sheet (rolls)
		Approx. 23 lm x 200 cm Art. no. 3093 --- 3 digit colour number
	ISO 24342	61 x 61 cm 14 tiles/box = 5.21 m ² Art. no. 3094 --- 3 digit colour number
	(box)	

TECHNICAL PERFORMANCES	STANDARDS	iQ Toro SC
Dimensional stability	ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles
Reaction to fire	EN ISO 13501-1 EN ISO 9239-1 EN ISO 11925-2	Class B _{fl} s1 ≥ 8 kW/m ² Pass
Residual indentation	ISO 24343-1	Required value: ≤ 0.10mm Best measured value: 0.02 mm
Castors chair test	ISO 4918	Suitable
Static electrical discharge	EN 1815	< 2 kV
Electrical insulation	VDE 0100, Part 600	R _i ≤ 5 x 10 ⁴ Ohms
Electrical resistance	ESD-approval SP-method 2472 EN 1081	R ≤ 10 ⁹ Ohms R ₁ 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms R ₂ 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms R 5x10 ⁴ ≤ R ≤ 10 ⁶ Ohms ≤ 3.5x10 ⁷ Ohms
Clean room test	ASTM F24 F51	Class A
Ease of decontamination	ISO 8690	Good
Total VOC emissions	AgBB/DIBt	≤ 10 µg/m ³ (after 28 days)
Underfloor heating		Suitable - max. 27°C
Thermal resistance	EN 12667	Approx. 0.01 m ² K/W
Light fastness	EN ISO 105-B02	≥ level 7
Chemical resistance	ISO 26987	Good resistance
Bacteria resistance	ISO 846:Part C	Does not favour growth
Slip resistance	DIN 51130 EN 13896	R9 ≥ 0.3
Seam strength	EN 684	Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
Colours		14


The above information is subject to modification for the benefit of further improvement. (05/16).

CUSTOMS TARIFF : 48205000000F

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



Logistics Information



General Information



According to European Classification ISO 10874 - EN 685



iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.
100	S 1002-Y50R	1287 322	104	S 1005-Y40R	1288 255	572	S 1515-Y30R	1287 438	576	S 4020-G50Y	1287 309
101	S 2502-B	1291 811	105	S 2020 Y30R	1292 372	573	S 2030-Y30R	1287 059	578	S 6502-B	1291 216
102	S 4502-B	1292 383	107	S 2020-R90B	1291 210	574	S 4005-Y50R	1287 379			
103	S 8502-B	1292 384	570	S 1502-Y50R	1287 531	575	S 7005-Y80R	1287 456			

■ **WESTERN EUROPE:** Austria: Tarkett Holding GmbH, Niederlassung Wien – Tel. +43 1 47 88 062 ■ Belgium: Tarkett France Belux – Tel. +32 16 35 98 80 ■ Denmark: Tarkett A/S – Tel. +45 43 90 60 11 ■ Finland: Tarkett Oy – Tel. +358 9 4257 9000 ■ France: Tarkett SAS – Tel. +33 1 41 20 42 49 ■ Germany: Tarkett Holding GmbH, Bereich Objekt – Tel. +49 62 33 810 ■ Greece: Tarkett Monoprosopi Ltd – Tel. +30 210 6745 340 ■ Italy: Tarkett S.p.A. – Tel. +39 0744 7551 ■ Luxembourg: Tarkett GDL SA – Tel. +352 949 211 8804 ■ Netherlands: Tarkett Holding GmbH, Vestiging Nederland – Tel. +31 416 685 491 ■ Norway: Tarkett AS – Tel. +47 32 20 92 00 ■ Portugal: Tarkett SA – Tel. +351 21 427 64 20 ■ Spain: Tarkett Floors S.L. – Tel. +34 91 358 00 35 ■ Sweden: Tarkett Sverige AB – Tel. +46 771 25 19 00 ■ Switzerland: Tarkett Holding GmbH, Bereich Objekt Schweiz – Tel. +41 043 233 79 24 ■ Turkey: Tarkett Aspen – Tel. +90 212 213 65 80 ■ United Kingdom: Tarkett Ltd – Tel. +44 (0) 1622 854 040 ■ **EASTERN EUROPE:** Baltic Countries: Tarkett Baltics – Tel. +370 37 262 220 ■ Czech Republic: Tarkett France SAS, org. slozka – Tel. +420-271 001 602 ■ Hungary: Tarkett France SAS – Tel. +36 1 437 8150 ■ Poland: Tarkett Polska Sp. z o.o. – Tel. +48 22 16 09 231 ■ Russian Federation: ZAO Tarkett RUS – Tel. +7 495 775 3737 ■ Slovakia: Tarkett France SAS, org. zlozka – Tel. +421 248 291 317 ■ South East Europe: Tarkett Trade d.o.o. – Tel. +381 21 7557 649 (44) 569 12 21 ■ Ukraine: Tarkett UA – Tel. +38 (0) 44 569 12 21 ■ **ASIA AND OCEANIA:** Australia: Tarkett Australia Pty Ltd – Tel. +61 2 88 53 12 00 ■ China: Tarkett Floor Covering (Shanghai) Co. Ltd. – Tel. +86 (21) 60 95 68 38 ext 841 ■ North East Asia: Tarkett Hong Kong Limited – Tel. +852 2511 8716 ■ India: Tarkett France (India Branch) – Tel. +91 11 4352 4073 ■ South East Asia: Tarkett Flooring Singapore Pte. Ltd. – Tel. +65 6346 1585 ■ **AFRICA:** Tarkett International: Tel. +33 1 41 20 41 01 ■ **MIDDLE EAST:** Tarkett Middle East: Tel. +961 1 51 3363/4 ■ Israel: Tarkett International: Tel. +33 1 41 20 41 01 ■ **NORTH AMERICA:** USA: Tarkett Inc. – Tel. +1 713 869 5811 / Johnsonite – Tel. +1 440 543 8916 ■ Canada: Tarkett Inc. – Tel. +1 450 293 173 ■ **LATIN AMERICA:** Brazil: Tarkett – Tel. 55 12 3954 7108 ■ Argentina - Chile - Uruguay: Tarkett Latam Mercosur – Tel. +54 11 47 08 0772 / +54 9 11 44 46 88 82 ■ Bolivia - Colombia - Ecuador - Panama - Paraguay - Peru - Trinidad and Tobago - Venezuela: Tarkett – Tel. +55 11 9 8410 9310 / +55 11 95494 0069 ■ Mexico / Central America: Tarkett Latam Mexico – Tel. +55 11 98410 9310



www.professionals.tarkett.com