

MULTIPAPER [160 g/m²]

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIX CoC 000010
Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706.
Bianco elevato. Superficie liscia. Effetto glossy. Ottima resa in fronte/retro. Ideale per stampa digitale a colori, stampa laser e inkjet, fotocopie di prestigio a colori e b/n.

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010
The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.
Superior whiteness. Smooth surface. Glossy effect. Excellent performance on front/back. Ideal for digital color printing, laser and inkjet printing, and color photocopies.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Umidità Assoluta Moisture Content	ISO 287 E.d.P.	%		4,5	5,5
Grammatura Grammage	UNI EN ISO 536 I.O. 10 P44 004	g/m ²	160,0	155,2	164,8
Spessore Thickness	ISO 534 I.O. 10 P44 005	microns		150,0	170,0
Grado di Bianco Brightness	ISO 2470 I.O. 10 P44 006	%	113,0	111,5	114,5
C.I.E. Whiteness C.I.E. Whiteness	ISO 11475 I.O. 10 P44 006		165,0	162,0	168,0
Opacità Opacity	ISO 2471 I.O. 10 P44 006	%		92,0	
Ruvidità [Bendtsen] Roughness [Bendtsen]	ISO 8791/2 I.O. 10 P44 007	ml/min		50,0	100,0