


BREDIK – underpants

Description

- Anti-torsion elastic band;
- Flat seams;
- 3D insulating weave to keep muscles warm;
- The elastic yarn grants ease of movements.



- The fabric thread guarantees excellent absorption and release of moisture, keeping skin always dry and the body at right temperature.
- This article has an antibacterial treatment carried out with biocides made of reaction mass of titanium dioxide and silver chloride. This treatment prevents the proliferation of bacteria, fungi and microorganisms that cause bad odours, guaranteeing long-lasting hygiene and freshness.



Maintenance

Maximum wash temperature: 30°C; Do not bleach; Do not dry in a tumble dryer; Do not iron; Do not dry clean.



DO NOT USE SOFTENER IN ORDER TO KEEP THE FUNCTIONAL PROPERTIES OF FIBERS UNCHANGED

item

V390-0-04 Anthracite

standards



THERMOREGULATING



BREATHABLE



ALL SEASONS



QUICK DRY



ANTIBACTERIAL



3D FABRIC



SEAMLESS



SLIM FIT

sizes

S-2XL


SAFETY TECHNICAL SPECIFICATIONS

	Test method	description	Cofra result	minimum requirement / range
Background fabric	EN ISO 1833-1977, Section 10	Composition:	67% Nylon 23% Polypropylene 10% Elastane	
	EN ISO 12127:1996	Weight per unit area	270 g/mq	

BRYNE – long-sleeved

Description

- The light fabric ondulation helps cold insulation thus preventing muscle ruptures;
- The 3D breathable weave easily releases moisture, cools even when high temperature or excessive movement cause over-sweating, assures the right body temperature in any weather;
- Anti-torsion elastic band;
- Flat seams;
- 3D insulating weave in the lumbar region to transport moisture outwards;
- The elastic yarn grants ease of movements.



- The fabric thread guarantees excellent absorption and release of moisture, keeping skin always dry and the body at right temperature.
- This article has an antibacterial treatment carried out with biocides made of reaction mass of titanium dioxide and silver chloride. This treatment prevents the proliferation of bacteria, fungi and microorganisms that cause bad odours, guaranteeing long-lasting hygiene and freshness.



Maintenance

Maximum wash temperature: 30°C; Do not bleach; Do not dry in a tumble dryer; Do not iron; Do not dry clean.



DO NOT USE SOFTENER IN ORDER TO KEEP THE FUNCTIONAL PROPERTIES OF FIBERS UNCHANGED

item

V391-0-04 Anthracite

standards



THERMOREGULATING



BREATHABLE



ALL SEASONS



QUICK DRY



ANTIBACTERIAL



3D FABRIC



SEAMLESS






SLIM FIT

sizes

S-2XL

SAFETY TECHNICAL SPECIFICATIONS

	Test method	description	Cofra result	minimum requirement / range
Background fabric	EN ISO 1833-1977, Section 10	Composition:	67% Nylon 23% Polypropylene 10% Elastane	
	EN ISO 12127:1996	Weight per unit area	270 g/mq	

Prague - bib			
Description	2 adjustable kneepad pockets, adjustable braces with quick release system, pen pocket, hammer loop, knee and leg ergonomic design, side pocket, rule pocket, breast zipped pocket, adjustable elasticated waist, YKK® zip, 2 back pockets, one of them with flap		
Maintenance	Maximum wash temperature: 60°C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Do not dry in a tumble dryer; Ironing at low temperature (max 110 °C). 	Item	V054-0-00 khaki/black V054-0-01 navy V054-0-02 royal blue/black V054-0-04 anthracite/black V054-0-05 black/black
		Standards	EN ISO 13688:2013 
		sizes	44 – 64

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background fabric	EN ISO 1833-1977, SECTION 10	Composition: cotton canvas Weave: Canvas plain 1/1	100% Warp: 8+8 [yarn/cm] Weft: 5+5 [yarn/cm]	
	EN ISO 12127:1996	Weight per unit area	250 g/sqm	
	EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
	ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 2.6 % weft: - 0.5 %	Max ± 3 % Max ± 3 %
	ISO 105X12: 2001	Colour fastness to rubbing	dry: 4 - 5 wet: 4	1 - 5 1 - 5
	EN ISO 105 B02: 1993, Method 3	Colour fastness to light	5	1 - 5

	ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4-5	1 – 5
	EN ISO 13934-2: 1999	Tensile strength	warp: 710 N weft: 560 N	400 N 400 N
	EN ISO 13688:2013 paragraph 4.2 (EN 1413)	The pH's determination from the watery extract	8.9	3,5<PH≤9,5
	EN ISO 13688:2013 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm

Port Louis - Jacket

Description

- jacket with buttons;
- 2 breast pockets.



Maintenance

Maximum temperature: 60°C; Do not bleach; Do not dry clean; Tumble drying possible; Drying at lower temperature; Ironing at low temperature (max 110°C).



item

V352-0-01 navy

V352-0-04 anthracite

standards







EN ISO 13688:2013

sizes

44 – 64

SAFETY TECHNICAL SPECIFICATIONS

	Test method	description	Cofra result	minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% cotton	
		Weave: Twill		
	EN ISO 12127:1996	Weight per unit area	270 gr/sqm	
	ISO 105X12	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3 - 4	1 - 5 1 - 5
	ISO 105-C06, C2S	Colour fastness to washes (60°C)	Colour change: 4-5 Staining: 4 – 5	1 - 5 1 - 5
	ISO-105-E04	Colour fastness to perspiration	Colour change: 4-5 Staining: 4-5	1 - 5 1 - 5
	ISO-105-X11	Colour fastness to hot pressing	Dry: 4-5 Wet: 4-5	1 - 5 1 - 5
	ISO 3071:2005	The pH's determination from the watery extract	pH : 7.4	3,5<PH≤9,5
	EN ISO 13688:2013 par. 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 6330 Test N0.2A	Dimensional change to washes	Warp: - 2.9 % Weft: - 2.9 %	+/- 3%
	EN ISO 13934-2	Tensile strength	Warp: 486.3 N Weft: 267.6 N	400 N 400 N
	ISO 13937-1	Tearing strenght	Warp: 22.15 N Weft: 14.24 N	25 N 25 N
	ISO 105 B02	Colour Fastness To Light	Colour change: > 5	

Namibia - coat			
Description	<ul style="list-style-type: none"> Smock with button closure; 2 wide front pockets; 1 breast pocket. 		
Maintenance	Maximum temperature: 60°C; Do not bleach; Do not dry clean; Tumble drying possible; Drying at lower temperature; Ironing at low temperature (max 110°C).     	item	V353-0-01 navy V353-0-04 anthracite
		standards	EN ISO 13688:2013
		sizes	44 – 64

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% cotton	
		Weave: Twill	Warp: 68x44 [yarn/inc] Weft: 10x10 [yarn/inc]	
	EN ISO 12127:1996	Weight per unit area	270 gr/sqm	
	ISO 105X12	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3 - 4	1 - 5 1 - 5
	ISO 105-C06, C2S	Colour fastness to washes (60°C)	Colour change: 4-5 Staining: 4 – 5	1 - 5 1 - 5
	ISO-105-E04	Colour fastness to perspiration	Colour change: 4-5 Staining: 4-5	1 - 5 1 - 5
	ISO-105-X11	Colour fastness to hot pressing	Dry: 4-5 Wet: 4-5	1 - 5 1 - 5
	ISO 3071:2005	The pH's determination from the watery extract	pH : 7.4	3,5<PH≤9,5
	EN ISO 13688:2013 par. 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 6330 Test N0.2A	Dimensional change to washes	Warp: - 2.9 % Weft: - 2.9 %	+/- 3%
	EN ISO 13934-2	Tensile strength	Warp: 486.3 N Weft: 267.6 N	400 N 400 N
	ISO 13937-1	Tearing strenght	Warp: 22.15 N Weft: 14.24 N	25 N 25 N
	ISO 105 B02	Colour Fastness To Light	Colour change: > 5	