



MHKMEDİKAL
TEKSTİL

Performance Characteristics of SURGICAL GOWNS

PRODUCT NAME		DISPOSABLE STERILE SURGICAL GOWNS			
Tests	Test Method	Unit	Specifications	Test Report / LAB	Evaluation
Resistance to microbial penetration — Dry	EN ISO 22612	CFU	≤ 300	18 / SANİTER	Acceptable
Resistance to microbial penetration — Wet	EN ISO 22610	/B	6,0	6,0/ SANİTER	Acceptable
Cleanliness — Particulate matter	EN ISO 9073-10	IPM	$\leq 3,5$	3,4/ SANİTER	Acceptable
Linting	EN ISO 9073-10	log10 (lint count)	≤ 4	3,6/ SANİTER	Acceptable
Resistance to liquid Penetration	EN 20811	cm H2O	≥ 100	315/ INTERTEK	Acceptable
Bursting strength — Dry	EN ISO 13938-1	kPa	≥ 40	123 / INTERTEK	Acceptable
Bursting strength — Wet	EN ISO 13938-1	kPa	≥ 40	122 / INTERTEK	Acceptable
Tensile strength — Dry	EN 29073-3	N	≥ 20	103 / INTERTEK	Acceptable
Tensile strength — Wet	EN 29073-3	N	≥ 20	106 / INTERTEK	Acceptable

**MHK MEDİKAL TEKSTİL**
ŞAN. VE TİC. LTD. ŞTİ.
Körkün Mahallesi Hidayet Caddesi No:23/1 Oğuzeli
Tif. 0342 341 93 66 Faks: 0342 341 93 67 GAZİANTEP
Tic.Sicil No: 40345 SUBURCU V.D.: 626 485 1520