



TMK-ARTROM S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119
 Tel: +40 (249) 436862, 434640, 434641
 Fax: +40 (249) 434330, 437288
 E-mail: office.slatina@tmk-artrom.eu www.tmk-artrom.eu
 EUID: ROONRC.J28/9/1991; J28/9/31.01.1991
 VAT No. RO 1510210/1992
 Subscribed and Paid Share Capital: 291.587.538,34 lei

INSPECTION CERTIFICATE - EN 10204: 2004 / 3.1

No: I 4341 Date: 31.05.2022	Manufacturer's mark:	Customer Order No.: 161	PL: 0790
CUSTOMER: NIMFA-COM SRL			
Specification: PED 2014/68/EU + EN10210-1:06/ EN10210-2:19/ EN 10216-2:13/ EN 10216-1:13		Dimensions: 57 x 4 x 6 000+100/-0 mm Steel: S355J2H / P265GH TC1 / P265TR2	
Description: Hot rolled seamless steel pipes with bevelled ends; unprotected; marking by painting at one end: manufacturer's mark, standard, steel grade, heat no, LOT, mill inspector no. 5, technical control sign			
Heat No.: R58462		Steel melt and rolled in ROMANIA	
Quantity delivered	Pcs.	Length - m	Weight- Kg
	74	444.00	2322

Ladle Chemical Analysis [%]

C	Mn	S	P	Si	Ni	Cr	Mo	Cu	Al	Nb	Ti	V	CE
0.19	1.22	0.003	0.010	0.19	0.09	0.06	0.03	0.18	0.025	0.001	0.001	0.002	0.430

Mechanical Properties

TENSILE TEST (EN ISO 6892-1) - at room temperature- Test Specimen / Strip-longitudinal			Rp0.2 N/mm ²	Rm N/mm ²	A %
Dimension (mm): 15.25 x 4.25			411	537	31
Section (mm ²): 65.16					
Length - (Lo) (mm): 45					
Drift expanding test (EN ISO 8493)	Flattening test (EN ISO 8492)	Charpy V - Notch (EN ISO 148-1)	Ring tensile test (EN ISO 8496)		
OK	OK	-	-		
Heat treatment: normalized during hot rolling process with temperature between 880-940°C Hydraulic test pressure - 70 bar for 5 sec: OK			Hardness HRB: 84-85 Hardness HRC max 22 (acc to NACE MR0175/ISO 15156) NACE MR0103/ISO 17945 Grain size ASTM E 112: 9.0		

Visual inspection and dimensional check: OK
 The manufacturer of pipes is certified in acc. with ISO 9001: 2015, ISO 14001:2015 and ISO 45001:2018
 NO WELD REPAIR ON HEREBY CERTIFIED TUBES
 The material "not contain intentional additions of elements such as lead, selenium, or sulphur to improve machinability"
Chief of QC & Testing of the Metallurgical Tubes Products
 Dipl. Eng. Silviu Barbulescu

MILL INSPECTOR
 Eng. Constantin Lupu

This MTC is digitally signed and sealed by TMK-ARTROM S.A. IT system. The document is valid without handwritten signatures.

CE 0036-CPR-M-008-2007	
TMK-ARTROM S.A. Draganesti Street, No.30, 230119, SLATINA, OLT, ROMANIA 22 No. 6-5E / CPR 18-05-22	
EN 10210-1:2006 S355J2H / 1.0576 intended to be used in metal structures or in composite metal and concrete structures	
Tolerances: Elongation: Tensile strength: Yield strength: Impact strength: Weldability: Durability: Dangerous substance: No performance determined	expressed as indicated in the DoP

THIS IS FOR CERTIFY THAT THE MATERIAL HEREIN DESCRIBED HAS BEEN MANUFACTURED WITH THE ORDERED SPECIFICATION AND THAT INFORMATION IS CORRECT, THEY MEET THE SPECIFICATION'S REQUIREMENTS AND ARE RECORDS IN OUR COMPANY DOCUMENTS.