

		ÇAMSAN ENTEGRE LAMINATE FLOORING QUALITY SPECIFICATIONS					
CHARACTERISTIC	STANDARD	8mm GLORIA [∞] - AC4 (EN STANDARD)	8mm GLORIA STAR - AC5 (EN STANDARD)	8mm LEGEND - AC5 (EN STANDARD)	12mm GLORIA - AC5 (EN STANDARD)	UNIT	
DENSITY	ÇAMSAN ENTEGRE	920 ± %3	920 ± %3	920 ± %3	920 ± %3	kg/m ³	
THICKNESS SWELLING		≤ %18	≤ %15	≤ %15	≤ %15	%	
WIDTH OF THE SURFACE LAYER (W)	TS EN 13329+A2	$\Delta W_{average} \leq 0,10$ $\Delta l_{average} \leq 0,10$, $W_{max} - W_{min} \leq 0,20$ $L_{max} - L_{min} \leq 0,20$	$\Delta W_{average} \leq 0,10$ $\Delta l_{average} \leq 0,10$, $W_{max} - W_{min} \leq 0,20$ $L_{max} - L_{min} \leq 0,20$	$\Delta W_{average} \leq 0,10$ $\Delta l_{average} \leq 0,10$, $W_{max} - W_{min} \leq 0,20$ $L_{max} - L_{min} \leq 0,20$	$\Delta W_{average} \leq 0,10$ $\Delta l_{average} \leq 0,10$, $W_{max} - W_{min} \leq 0,20$ $L_{max} - L_{min} \leq 0,20$	mm	
LENGTH OF THE SURFACE LAYER (l)		$1 \leq 1500 : \Delta l \leq 0,5$ mm, $1 > 1500 : \Delta l \leq 0,3$ mm/m.	$1 \leq 1500 : \Delta l \leq 0,5$ mm, $1 > 1500 : \Delta l \leq 0,3$ mm/m.	$1 \leq 1500 : \Delta l \leq 0,5$ mm, $1 > 1500 : \Delta l \leq 0,3$ mm/m.	$1 \leq 1500 : \Delta l \leq 0,5$ mm, $1 > 1500 : \Delta l \leq 0,3$ mm/m.	mm	
SQUARENESS OF THE ELEMENT (q)		$q_{max} \leq 0,20$	$q_{max} \leq 0,20$	$q_{max} \leq 0,20$	$q_{max} \leq 0,20$	mm	
STRAIGHTNESS OF THE SURFACE LAYER (s)		$S_{max} \leq 0,30$	$S_{max} \leq 0,30$	$S_{max} \leq 0,30$	$S_{max} \leq 0,30$	mm / m	
FLATNESS OF THE ELEMENT (f)		$f_{w, concave} \leq \% 0,15$, $f_{w, convex} \leq \% 0,20$ $f_{l, concave} \leq \% 0,50$, $f_{l, convex} \leq \% 1,00$	$f_{w, concave} \leq \% 0,15$, $f_{w, convex} \leq \% 0,20$ $f_{l, concave} \leq \% 0,50$, $f_{l, convex} \leq \% 1,00$	$f_{w, concave} \leq \% 0,15$, $f_{w, convex} \leq \% 0,20$ $f_{l, concave} \leq \% 0,50$, $f_{l, convex} \leq \% 1,00$	$f_{w, concave} \leq \% 0,15$, $f_{w, convex} \leq \% 0,20$ $f_{l, concave} \leq \% 0,50$, $f_{l, convex} \leq \% 1,00$	mm	
OPENING BETWEEN ELEMENTS(O)		$O_{average} \leq 0,15$, $O_{max} \leq 0,20$	mm				
HEIGHT DIFFERENCE BETWEEN ELEMENTS		$h_{average} \leq 0,10$, $h_{max} \leq 0,15$	mm				
SURFACE SOUNDNESS		TS EN 13329 / TS EN 311	≥ 1,25	≥ 1,25	≥ 1,25	≥ 1,25	N / mm ²
HUMIDITY		TS EN 322	%4 ≤ H ≤ %10 $H_{max} - H_{min} \leq \%3$	%4 ≤ H ≤ %10 $H_{max} - H_{min} \leq \%3$	%4 ≤ H ≤ %10 $H_{max} - H_{min} \leq \%3$	%4 ≤ H ≤ %10 $H_{max} - H_{min} \leq \%3$	%
FREE FORMALDEHYDE AMOUNT	TS EN 12460-3	E0: ≤ 1,75 E1: 1,75 < x ≤ 3,50	E0: ≤ 1,75 E1: 1,75 < x ≤ 3,50	E0: ≤ 1,75 E1: 1,75 < x ≤ 3,50	E0: ≤ 1,75 E1: 1,75 < x ≤ 3,50	mg / m ² . h	
DIMENSIONAL VARIATIONS AFTER CHANGES IN RELATIVE HUMIDITY	TS EN 13329 / TS EN 318	$\delta l_{average} \leq 0,9$, $\delta W_{average} \leq 0,9$	$\delta l_{average} \leq 0,9$, $\delta W_{average} \leq 0,9$	$\delta l_{average} \leq 0,9$, $\delta W_{average} \leq 0,9$	$\delta l_{average} \leq 0,9$, $\delta W_{average} \leq 0,9$	mm	
ABRASION RESISTANCE	TS EN 13329	AC4; ≥ 4000	AC5; ≥ 6000	AC5; ≥ 6000	AC5; ≥ 6000	Rev	
SMALL-DIAMETER BALL IMPACT RESISTANCE	TS EN 17368	≥ 35 mm	≥ 70 mm	≥ 70 mm	≥ 70 mm	N, mm	
LARGE-DIAMETER BALL IMPACT RESISTANCE	TS EN 13329 / TS EN 438-2	≥ 750 mm	≥ 1000 mm	≥ 1000 mm	≥ 1000 mm		
RESISTANCE TO STAINING	TS EN 438-2	5 (group 1 ve group 2), 4 (group 3)	5 (group 1 ve group 2), 4 (group 3)	5 (group 1 ve group 2), 4 (group 3)	5 (group 1 ve group 2), 4 (group 3)	Class	
EFFECT OF A CASTOR CHAIR	TS EN 425	25.000 cycles - no damage	No change in appearance or damage	25.000 cycles - no damage	25.000 cycles - no damage	View	
EFFECT OF A FURNITURE LEG	TS EN 424	No damage shall be visible	View				
APPEARANCE, SURFACE DEFECTS	TS EN 438-2	Minor surface defects as defined in the EN 438 series are permitted.	Minor surface defects as defined in the EN 438 series are permitted.	Minor surface defects as defined in the EN 438 series are permitted.	Minor surface defects as defined in the EN 438 series are permitted.	View	
STATIC INDENTATION	TS EN ISO 24343-1	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	mm	
LIGHT FASTNESS	TS EN 20105	Not worse than 4	Class				
LOCKING RESISTANCE	ISO 24334	Fl ≥ 1 kN/m Fs ≥ 2 kN/m	N / mm ²				

GENEL MÜDÜRLÜK / HEAD OFFICE

Büyükdere Cad. Eski Oto Sanayi
Emektar Sok. No:4 K:2 4. Levent
Kağıthane/ İstanbul / TÜRKİYE
Tel : +90 212 284 62 43
Faks : +90 212 284 62 45

FABRİKA / FACTORY

Sakarya II. Organize San. Bölgesi
Hendek / Sakarya / TÜRKİYE
Tel : +90 264 654 58 18
Faks : +90 264 654 58 16

www.camsan.com

www.parkelam.com

V.D. Yenikapı

V.D. NO: 228 005 3797

Mersis No: 0228005379700014