




TMK-ARTROM S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119
 Tel: +40 (249) 436862, 434640, 434641
 Fax: +40 (249) 434330, 437288
 E-mail: office.slatina@tmk-artrom.eu www.tmk-artrom.eu
 EUID: ROONRC.J28/9/1991; J28/9/31.01.1991
 VAT No. RO 1510210/1992
 Subscribed and Paid Share Capital: 291.587.538,34 lei

INSPECTION CERTIFICATE - EN 10204: 2004 / 3.1

No: I 7743 Date: 06.12.2022	Manufacturer's mark: 	Customer Order No.: 183	PL: 1611
CUSTOMER: NIMFA-COM SRL			
Specification: EN 10210-1:06/ EN 10210-2:19/ EN 10216-3:13/ EN 10216-2:13/ EN 10216-1:13		Dimensions: 48.3 x 3.2 x 12 000+100/-0 mm Steel: S355J2H/ P355NL1 TC1/ P265GH TC1/ P265TR2	
Description: Hot rolled seamless steel pipes; unprotected; marking by painting at one end: manufacturer's mark, standard, steel grade, heat no, LOT, LENGTH (m), mill inspector no. 5, technical control sign			
Heat No.: R59547		Steel melt and rolled in ROMANIA	
Quantity delivered	Pcs.	Length - m	Weight- Kg
	70	840.0	2970

Ladle Chemical Analysis [%]

C	Mn	S	P	Si	Ni	Cr	Mo	Cu	Al	Nb	Ti	V	CE
0.18	1.20	0.003	0.012	0.24	0.08	0.08	0.02	0.25	0.023	0.001	0.001	0.002	0.422
Cr+Cu+Mo+Ni=0.43				Nb+V=0.003				Nb+V+Ti=0.004				N=0.009	

Mechanical Properties

TENSILE TEST (EN ISO 6892-1) - at room temperature- Test Specimen / Strip-longitudinal			Rp0,2 N/mm ²	Rm N/mm ²	A %
Dimension (mm): 15.60 x 3.30			406	548	32
Section (mm ²): 52.52					
Length - (Lo) (mm): 40					
Drift expanding test (EN ISO 8493)	Flattening test (EN ISO 8492)	Charpy V - Notch (EN ISO 148-1)	Ring tensile test (EN ISO 8496)		
OK	OK	-	-		
Heat treatment: normalized temperature between 880-940°C			Melting process: electric arc furnace, fully killed		
Test Eddy Current cf. EN ISO 10893-1: OK					

Visual inspection and dimensional check: OK
 The manufacturer of pipes is certified in acc. with ISO 9001: 2015, ISO 14001:2015 and ISO 45001:2018
NO WELD REPAIR ON HEREBY CERTIFIED TUBES
 The material "not contain intentional additions of elements such as lead, selenium, or sulphur to improve machinability"
Chief of QC & Testing of the Metallurgical Tubes Products
 Dipl. Eng. Silviu Barbulescu



MILL INSPECTOR

Eng. Constantin Lupu



This MTC is digitally signed and sealed by TMK -ARTROM S.A. IT system. To check its authenticity and integrity, please scan the QR code to download the original electronic document from our site. If you already received an electronic copy from your supplier, please make sure that the file is digitally signed by TMK- ARTROM S.A. Falsification of this document is punishable under the legal provisions and entitles us to claim damages

THIS IS FOR CERTIFY THAT THE MATERIAL HEREIN DESCRIBED HAS BEEN MANUFACTURED WITH THE ORDERED SPECIFICATION AND THAT INFORMATION IS CORRECT, THEY MEET THE SPECIFICATION'S REQUIREMENTS AND ARE RECORDS IN OUR COMPANY DOCUMENTS.

	
0036- CPR-M-008-2007	
TMK-ARTROM S.A. Draganesti Street, No.30, 230119, SLATINA, OLT, ROMANIA	
22 No. 6-5E / CPR 18-10-22	
EN 10210-1:2006	
S355J2H / 1.0576	
intended to be used in metal structures or in composite metal and concrete structures	
Tolerances: Elongation: Tensile strength: Yield strength: Impact strength: Weldability: Durability:	expressed as indicated in the DoP
Dangerous substance: No performance determined	