

REPORT NUMBER:





TEST REPORT

Number :

Applicant :

Date : Dec 11, 2020

Sample Description As Declared :

No. Of Sample : One  
Fibre Content : -  
Material : One Piece Of Synthetic Material  
Finishing : -  
End Uses : -  
Colour : 2230  
Style No. : FLY  
Order No./PO No. : -  
Buyer's Name : -  
Manufacturer's Name : -  
Ref. : -

Applicant's Provided Care Instruction/Label :

Date Sample Received : Dec 07, 2020  
Date Testing Started : Dec 07, 2020

---

Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai



---

Baron Hu  
Senior Manager of Footwear Lab



TEST REPORT

Number :

Tests Conducted (As Requested By The Applicant)

- 1 Color Fastness To Light (AATCC 16.3-2014, Option 3, Xenon-Arc Lamp):

40 AATCC Fading Unit (AFU) Exposure

Grade

4.5 Grade

- 2 Color Fastness To Crocking (AATCC TM8-2016e):

Dry

4.5

Wet

4.5

- 3 Tensile Strength As Received (ASTM D5034-09(2017), 1-in Grab Test, Tensile Testing Machine, CRE):

Warp

181.0 lbf

Weft

153.5 lbf

- 4 Seam Slippage As Received (ASTM D434-1995, Tensile Testing Machine, CRE):

S.O. 1/4"

// To Warp

\*

// To Weft

\*

Strength

// To Warp

81.0 lbf(FTS)

// To Weft

81.9 lbf(FTS)

Remark : S.O. 1/4" = Seam opened at 1/4 inch

FTS = Fabric torn at seam

\* = The seam opening was less than 1/4 inch though the ultimate seam strength was found as stated.



TEST REPORT

Number :

Tests Conducted (As Requested By The Applicant)

5    Abrasion Resistance (ASTM D4966-12(2016), Option 1, Martindale Abrasion And Pilling Tester, 12 kPa Total Pressure):

<div>Resistance</div> <div>Face Side</div>	Over 100,000 Rubs
--	-------------------

End of Report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

*This report shall not be reproduced except in full, without written approval of the laboratory.*