


| | | |
|-------------------------|---|----------------------|
| Description | Name of fabric | Twill fabric 3/2 |
| | End - Use | Cleanroom |
| | Cleanroom Class | |
| | ISO | 4 - 8 |
| | EU GMP | A - C |
| | US FED Std | 10 - 100.000 |
| | Weight | 118 g/m ² |
| | Fabric composition | 98% PES / 2% CA |
| | Type of antistatic yarn | Negastat P210 |
| | Finish | |
| | Weave | Twill 3/2 |
| | Pattern | Grid 5mm * 5mm |
| | Sterilisation | Steam - Gamma |
| Available colors |  | |
| User comfort | High filtration Soft feeling Very comfortable to wear | |

| | | |
|-------------|--|---------------------------|
| Performance | Air permeability according to ISO 9237-2 1995 | 18,10 l/m ² .s |
| | Water vapour permeability according to ISO 11092:2014 Ret | 2,71 m ² Pa/W |
| | Tensile strength according to ISO 13934/1:2013 | Warp 830 N / Weft 1500 N |
| | Abrasion according to ISO 12947/2:1998 | > 100.000 cycles |
| | Decay time according to EN 1149-3 | 0,01 sec |
| | Surface resistivity according to EN 1149-1 | 10 exp6 Ohm |
| | Filtration effect | |
| | by 0,3 µm | 98% |
| by 0,5 µm | 98% | |
| by 1 µm | 98% | |