## **Technical specifications**

Marmoleum meets the requirements of EN-ISO 24011 Marmoleum Acoustic meets the requirements of EN 687 Marmoleum Decibel meets the requirements of EN 686



	Marmoleum Decibel me	eets the requireme	Marmoleum Real/Fresco 2.0 mm	Marmoleum Real/Fresco/Vivace/ Splash/Terra 2.5 mm	Marmoleum Real/Fresco 3.2 mm	Marmoleum Decibel	Marmoleum Acoustic	
° ×	Total thickness	EN-ISO 24346	2.0 mm	2.5 mm	3.2 mm	3.5 mm	4.0 mm	
	Surface finish		Topshield Pro	Topshield Pro	Topshield Pro	Topshield Pro	Topshield Pro	
ĺ₩ ∰	Domestic use	EN-ISO 10874	Class 23	Class 23	Class 23	Class 23	Class 23	
	Commercial use	EN-ISO 10874	Class 32	Class 34	Class 34	Class 33	Class 33	
[hi _iii	Light industrial use	EN-ISO 10874	Class 41	Class 43	Class 43	Class 41	Class 41	
	Collection size		29 colours	90 colours	8 colours	14 colours All items available as made to order	6 colours	
T	Roll width	EN-ISO 24341	2.00 m	2.00 m	2.00 m	1.90 / 2.00 m	2.00 m	
<b>⇒</b>	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m	
ñ	Total weight Typical value	EN-ISO 23997	2300 g/m <sup>2</sup>	2900 g/m <sup>2</sup>	3900 g/m²	3100 g/m²	4000 g/m²	
۰ لو	Residual indentation Typical value	EN-ISO 24343-1	≤ 0.15 mm ~0.07 mm	≤ 0.15 mm ~0.08 mm	≤ 0.15 mm ~0.10 mm	≤ 0.30 mm ~ <i>0.20 mm</i>	≤ 0.40 mm ~0.25 mm	
6	Castor chair continuous use	ISO 4918/EN 425	Suitable for office chairs with castors					
R	Light fastness EN-ISO 105-B02 Method 3: blue scale minimum 6							
52	Flexibility	EN-ISO 24344	ø 30 mm	ø 40 mm	ø 50 mm	ø 40 mm	ø 60 mm	
\$0	Resistance to chemicals	EN-ISO 26987	Resistant to dil	uted acids, oils, fats and to th	e conventional solvents. No	t resistant to prolonged exp	osure to alkalis	
	Bacteriostatic properties*	ies* Marmoleum has natural bacteriostatic properties which are confirmed by independent laboratories, even against the bacteria MRSA						
<b>S</b>	Cigarette resistance	tte resistance EN 1399 There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result of stubbed-out cigarettes can be removed						
K.	Slip resistance	DIN 51130	R9	R9	R9	R9	R9	
57 1040	Electrical resistance Marmoleum Ohmex	EN 1081	-	1-10 <sup>6</sup> < R1 < 1-10 <sup>8</sup> Ω static dissipative	-	-	-	
٩	Acoustical impact sound reduction	EN-ISO 717-2	≤ 4 dB	≤ 5 dB	≤ 6 dB	≤ 18 dB	≤ 14 dB	
LCA	Life Cycle Assessment		LCA is the foundation for securing the lowest environmental impact					
Ì	Creating Better Environm	ents						
marmoleum	Climate positive		Marmoleum 2.0mm and 2.5mm are produced climate positive (cradle to gate)**					
$\prec$	renewable electricity Marmoleum is manufactured using 100% electricity from renewable sources							
	natural materials – (e.g. linseed oil, jute, tree resin, wood flour, limestone) –		Marmoleum is made of 94-98% natural materials					
			Marmoleum contains PEFC certified wood flour					
•			Marmoleum is free of PVC, PET, synthetic rubber and plasticizers					
	recycled content		Marmoleum contains recycled content					
Ë	Application on underfloor h	neating	yes	yes	yes	yes	yes	
	Marmoleum meets the requirements of EN 14041							
(6	Product code	EN 14041	0100201_DoP_306	0100201_DoP_306	0100201_DoP_306	0100207_DoP_306	0100206_DoP_306	
G Girst CS	Reaction to fire	EN 13501-1	C <sub>n</sub> -s1, G, CS	C <sub>fl</sub> -s1, G, CS***	C <sub>fl</sub> -s1, G, CS	C <sub>fl</sub> -s1, G, CS	C <sub>fl</sub> -s1, G, CS	
°9€5 ≥0.30	Slip resistance	EN 13893	$\mu \geq 0.30$	μ≥0.30	$\mu \ge 0.30$	$\mu \ge 0.30$	$\mu \ge 0.30$	
ダン 本 2011	Body voltage	EN 1815	≤ 2 kV	≤ 2 kV	$\leq 2 \text{ kV}$	≤ 2 kV	≤ 2 kV	
λ <sub>23</sub> <i>t t t</i>	Thermal resistance	EN 12524	0.17 W/m·K	0.17 W/m·K	0.17 W/m·K	0.17 W/m·K	0.17 W/m·K	
	Indoor Air Emissions: TVOC at 28 days	EN 16516	< 0.05 mg/m <sup>3</sup>	< 0.05 mg/m <sup>3</sup>	< 0.05 mg/m <sup>3</sup>	< 0.05 mg/m <sup>3</sup>	< 0.05 mg/m <sup>3</sup>	
	Content of specific dangerous substances	EN 14041	Compliant, not actively added	Compliant, not actively added	Compliant, not actively added	Compliant, not actively added	Compliant, not actively added	

\*Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions. \*\*\*Marmoleum 2.5mm is available in reaction to fire classification  $B_{\mu}$  s1, G, CS. Available on request, contact sales support for leadtime.

Recommended adhesives: For the latest installation instructions and recommended adhesives

## please visit www.forbo-flooring.co.uk/installation

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites. Marmoleum is manufactured in a facility certified to SA8000 and OHSAS 18001.

R ISO 9001 Whilst Forbo Flooring UK Limited does its best to ensure that the contents of this specification A set of the formation of the set not represent that the information is accurate, complete or current.





For more information:

e: info.flooring.uk@forbo.com

- t: 0800 121 4780
- w: forbo-flooring.co.uk/marbled

