

Eco-210

65% RECYCLED POLYESTER /
35% RECYCLED COTTON /
210 GSM / TWILL 2/1



| | |
|---------------------|---|
| Fabric name | Eco-210 |
| Fabric weight | 210 ± 5 gsm |
| Composition | 65% Recycled Polyester, 35% Recycled Cotton |
| Full width | 152 ± 2 cm |
| Weave | twill 2/1 |
| Finishes | WR |
| Area of use | construction and transport sectors work wear |
| Washing instruction | |

Physical properties*

| | | | warp | weft | |
|---|---|------------------|-----------------|------|--|
| 1 | Tensile strength, N | ISO 13934-1:2013 | 1600 | 360 | |
| 2 | Tearing strength, N | ISO 13937-3:2000 | 30 | 20 | |
| 3 | Dimensional Stability To Washing, max. | ISO 6330:2000 | 3.0% | 3.0% | |
| 4 | Abrasion Resistance | ISO 12947-2:2002 | > 30 000 | | |
| 5 | Pilling Resistance (after 1000 rev.) | ISO 12945-2:2000 | 3-4 | | |
| 6 | Colour Fastness To Washing (cotton+polyester) 60°C, min. | ISO 105-C06:2010 | | | |
| | | | Colour change | 4 | |
| | | | Colour staining | 3 | |
| 7 | Colour Fastness To Perspiration, min. | ISO 105-E04:2013 | | | |
| | | | Colour change | 4 | |
| | | | Colour staining | 4 | |
| 8 | Colour Fastness To Rubbing, min. | ISO 105-X12:2001 | | | |
| | | | Dry | 3-4 | |
| | | | Wet | 2-3 | |
| 9 | Colour Fastness To Light | ISO 105-B02:2013 | > 4 | | |

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com

Test Report No.: 0154096991a 001

Page 1 of 5

Client: SHANGHAI XM GROUP LTD

Office 2403~2403, 24th Floor, Zhongyi International Commercial Plaza, 1833
Zhongshan North Road, Shanghai, China

Contact Person: Anna He

Sample Description As Declared :

No. Of Sample : One (1)
Sample Description : Econom-210TC 70/30 210gsm twill 2/1, Navy

**Applicant's Provided
Care Instruction/Label:**



Sample Receiving date: 2015-04-28
Delivery condition: Apparent good, Samples tested as received
Test Period: 2015-04-28 to 2015-05-05

For and on behalf of
TÜV Rheinland (Shanghai) Co., Ltd.



2015-05-05 Tina Wu / Department Manager

Date

Name/Position

*Test result is drawn according to the kind and extent of tests performed.
This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.*

Conclusion

Banned Azo Dyes

M001
P

Note : P = Pass
= No Comment
N/A = Not Applicable

F = Fail
- = Did Not Perform
* = See Remark

Material list

| Material No. | Material | Color | Location |
|--------------|----------|-------|--------------|
| M001 | Textile | Navy | Woven fabric |

1. Banned Azo Dyes

Test Method: EN 14362-1:2012

Test Result:

| Test No. | Material No. | Method | Unit | RL | Customer requirement | Test Result | Conclusion |
|----------|--------------|------------|-------|----|----------------------|-------------|------------|
| 1 | M001 | EN 14362-1 | mg/kg | 5 | 30 | A11: 6 | Pass |

Abbreviation: n.d. = not detected (< Reporting Limit)
RL = Reporting Limit
mg/kg = milligram per kilogram

Remark:

- * The CAS-number 97-56-3 (A5) and 99-55-8 (A6) are further reduced to CAS-number 95-53-4 (A18) and 95-80-7 (A19).
- ** Azo colorants that are able to form CAS-number 60-09-03 (A22), generate under the condition of this method CAS-number 62-53-3 (A25) and 106-50-3 (A26).
- *** Azo colorants that are able to form 4-aminoazobenzene (A22), is confirmed by EN 14362-3:2012 / ISO 17234-2:2011.
- **** Azo colorants are detected & quantified by GC/MS and confirmed by LC/MS.


List of azo colorants being tested (according to REACH regulation (EC) No. 1907/2006 and amendment no. 552/2009 Annex XVII Item 43 (formerly known as 2002/61/EC)):

| ID | Azo colorant | CAS No. |
|-------|---|----------|
| A1 | biphenyl-4-ylamine / 4-aminobiphenyl / xenylamine | 92-67-1 |
| A2 | benzidine | 92-87-5 |
| A3 | 4-chloro-o-toluidine | 95-69-2 |
| A4 | 2-naphthylamine | 91-59-8 |
| A5* | o-aminoazotoluene / 4-amino-2',3'-dimethylazobenzene / 4-o-tolylazo-o-toluidine | 97-56-3 |
| A6* | 5-nitro-o-toluidine | 99-55-8 |
| A7 | 4-chloroaniline | 106-47-8 |
| A8 | 4-methoxy-m-phenylenediamine | 615-05-4 |
| A9 | 4,4'-methylenedianiline / 4,4'-diaminodiphenylmethane | 101-77-9 |
| A10 | 3,3'-dichlorobenzidine / 3,3'-dichlorobiphenyl-4,4'-ylenediamine | 91-94-1 |
| A11 | 3,3'-dimethoxybenzidine | 119-90-4 |
| A12 | 3,3'-dimethylbenzidine / 4,4'-bi-o-toluidine | 119-93-7 |
| A13 | 4,4'-methylenedi-o-toluidine | 838-88-0 |
| A14 | p-cresidine | 120-71-8 |
| A15 | 4,4'-methylene-bis-(2-chloro-aniline) / 2,2'-dichloro-4,4'-methylene-dianiline | 101-14-4 |
| A16 | 4,4'-oxydianiline | 101-80-4 |
| A17 | 4,4'-thiodianiline | 139-65-1 |
| A18 | o-toluidine / 2-aminotoluene | 95-53-4 |
| A19 | 4-methyl-m-phenylenediamine | 95-80-7 |
| A20 | 2,4,5-trimethylaniline | 137-17-7 |
| A21 | o-anisidine / 2-methoxyaniline | 90-04-0 |
| A22** | 4-aminoazobenzene | 60-09-03 |
| A25 | aniline | 62-53-3 |
| A26 | 4-aminoaniline | 106-50-3 |

Sample Photo:



- END -



**STANDARD
100**

**BEWO 084394
TESTEX**

**This certificate BEWO 084394 is valid until
15.08.2025.**

SUPPORTING DOCUMENTS

- ✓ Test report : BJ015 245163.1
- ✓ Declaration of conformity in accordance with EN ISO 17050-1 as required by OEKO-TEX®
- ✓ OEKO-TEX® Terms of Use (ToU)

A handwritten signature in blue ink, appearing to read "M. Bachmann", written over a horizontal line.

**Matz Bachmann
Managing Director**

A handwritten signature in blue ink, appearing to read "D. Ajdinovic", written over a horizontal line.

**Dijana Ajdinovic
Ecology Team Leader**