

STOBITAN® P 16 mm

2-layer system – SBR & EPDM



Support porous macadam / concrete

	Product	Quantity kg/m ²
Primer	Stobielast® S 100.00 or Stobielast® S 080.00 (1 component)	0.15 kg
Base layer 8 mm	Stobielast® S 135/S 131.87 (1 component) SBR rubber 1- 4 mm	1.20 kg 5.60 kg
Surface 8 mm	Stobielast® S 135/S 131.87 (1 component) EPDM rubber 1-3 mm	1.35 kg 7.50 kg
Total thickness		ar. 16 mm

Information In case the surface layer will be built in light colours (light blue, light grey, white etc.) we recommend to use lightfast binders for the surface layer. Please consult our technical service.

Applications Multisport facilities

Test Reports & Certificates IAAF Test report
DIN18035 Part 6 : Environmental compatibility
EN 14877: 2013 : European Sport Specifications

Stockmeier Uréthanes France SAS
8, Rue de l'Industrie
Z.I. Est
68700 Cernay
FRANCE
T +33 (0)3 89 75 70 70
F +33 (0)3 89 75 70 81
snad@snad.fr
urethanes.fr@stockmeier.com
www.stockmeier-urethanes.com

Issue October 2014