



International Chem-Crete Inc.
800 Security Row Ste 1, Richardson, TX 75081, U.S.A
Tel: (972) 671-6477, Fax: (972) 238-0307

Chem-Crete Europe, s.r.o.
Stanicna 13, 90851 Holic, Slovakia
Tel: +421 34 668 3181 Fax: +421 34 668 3119

contact-us@chem-crete.com • www.chem-crete.com

The following are typical test results for CHEM-CRETE ASP FLEX 4 crack filler:

PROPERTY	TYPICAL TEST RESULTS
Penetration, 200g, 60 sec. 39.2 ± 0.2 F, dmm:	30
Penetration, dmm:	42
Resilience, %:	50
Flow, cm:	0.1
Ductility, cm:	33
Softening Point, °F:	205
Tensile Adhesion, %:	500+
Asphalt Compatibility:	Pass
Bitumen Content, %:	60+
Flexibility @ 30 °F:	Pass
Wt./Gal., Lb.:	9.8
Viscosity, CPS @ 380 °F:	8,000
Recommended Pouring Temperature:	380 °F
Maximum Safe Heating Temperature:	400 °F
VOC Content, g/L:	0

CHEM-CRETE ASP FLEX 4 complies with the requirements of ASTM D5078-90.

Name: _____

Title: _____

Date: _____