

CHIRASORB

CHIRASORB is a mid-term absorbable, coated, synthetic, multifilament suture made of 90% glycolide and 10% L-lactide. The substances contained in the coating and suture are nonantigenic and noncollagenous.

Sterile Chirasorb is available in violet or natural. The product elicits a minimal acute inflammatory reaction in tissues.

Progressive loss of tensile strength and absorption of Chirasorb occurs by hydrolysis, when the polymer is degraded to glycolic and lactic acids, which are subsequently absorbed and metabolised by the body.



General surgery, Gynaecology, Ophthalmic, Skin Closure (e.g. intracutaneous, Indication:

subcutaneous), Muscular layer and Ligation.

Chirasorb should not be used in tissues subject to expansion, stretching or distension, Contraindication:

or which might require long-term mechanical support.

10/0 to 6 USP Sizes:

Multifilament Structure:

Absorption method: Hydrolysis

Strength Retention

MID-TERM HEALING (35 days) Profile:

> 100% 1 Day 14 Days 75% 21 Days 50%

Mass Absorption profile:

56 - 70 days

UK03

65



Absorbable - Chirasorb

CHIRASORB

UK03 **68**

asorb	
Chir	
able -	
Absorb	

Needle	EP	USP	Length	Colour	Cat. No	information
HR: 1/2 circle, rou	nd body needle					
HR 22 A	2	3/0	6 x 45 cm	Violet	LV 0327	Take-off needle
HR 25	5	2	1 x 75 cm	Violet	LV 0297	*
HR 26	3	2/0	1 x 45 cm	Violet	LV 0136	
	2 3 3.5	3/0 2/0 0	1 x 75 cm 1 x 75 cm 1 x 75 cm	Violet Violet Violet	LV 0535 LV 0536 LV 0540	
HR 26 A	2	3/0	6 x 45 cm	Violet	LV 0347	Take-off needle
	1.5	4/0	1 x 45 cm	Violet	LV 0245	
- NT	2 3	3/0 2/0	6 x 45 cm 6 x 45 cm	Violet Violet	LV 0537 LV 0538	
	1.5 2 3 3.5 4	4/0 3/0 2/0 0 1	1 x 75 cm 1 x 75 cm 1 x 75 cm 1 x 75 cm 1 x 75 cm	Violet Violet Violet Violet Violet	LV 0265 LV 0266 LV 0267 LV 0268 LV 1269	
	2 3	3/0 2/0	1 x 90 cm 1 x 90 cm	Violet Violet	LV 0366 LV 0367	
HR 27 A	3	2/0	6 x 45 cm	Violet	LV 0338	Take-off needle,
	€ 2	3/0	4 x 75 cm	Violet	LV 0639	Take-off needle