



Chemical and stain resistance of Grabo Fortis homogeneous flooring

Method: liquid test material was dropped on the surface by pipette and let it and after testing period we cleaned the surface with clean water and then wiped off with dry cloth.

Grabo Fortis resists to the following materials for 24 hours, no stains, no any damage, no discoloration was experienced.

- Kiehl Alkona-concentrated hospital cleaning material
- Tevasept Skin- polyalcohol hospital disinfectant
- Betadine disinfectant solution
- Cooking oil (sunflower)
- Ketchup
- Mustard
- Hydrogen peroxide solution (disinfectant)
- Hypo (Natrium-hypochlorite, disinfectant)
- Domestos (disinfectant)
- 10% acetic acid solution
- benzene

Grabo Fortis resists to the following materials for 1 hour, no stains, no any damage, no discoloration was experienced.

- Eosin solution (red pigment)
- Descaling solution
- Hungarian red paprika cream

2016.02.08.



GRABOPLAST | FLOOR COVERING MANUFACTURERS LTD.

Fehérvári St. 16/b, Győr, 9023

Phone: +36 96 506 100, Fax: +36 96 506 196 | E-mail: mail@graboplast.hu

Reg. number: 08-10-001859 | Tax number: 14986042-2-08

VAT number: HU14986042

WWW.GRABOPLAST.COM