

Technical Data Sheet

updated
checked

12.09.2023
12.09.2023

Product	Satinette Double
	6669KMX2 with additional PU-coating, double-sided printable
Material	100 % Polyester
Stock widths	app. 305 cm
Making-up	rolled on paper cores
Packaging	wrapped with foil
Ink-type	transfer printing
characteristics	air tight, blockout, shiny, water repellent

Weight				
acc. to DIN EN 12127	450.00	[g/m ²]	+- 5	[%]

Shrinkage

Heat Shrinkage, 195 °C, 90 sec, lengthwise				
acc. to AA 25-02	-3.00	[%]	+- 1	[%]

Heat Shrinkage, 195 °C, 90 sec, crosswise				
acc. to AA 25-02	-1.00	[%]	+- 1	[%]

Tearing strength

Elongation at 100 N, longitudinal direction				
acc. to DIN EN ISO 13934-1	5.50	[%]	+- 20	[%]

Elongation at 100 N, cross direction				
acc. to DIN EN ISO 13934-1	1.00	[%]	+- 20	[%]

Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	70.00	[%]	+- 20	[%]

Maximum tensile elongation, cross direction				
acc. to DIN EN ISO 13934-1	36.00	[%]	+- 20	[%]

Georg+Otto Friedrich

TEXTILES. MADE IN GERMANY.

Maximum tearing strength, longitudinal
direction (min.)

acc. to DIN EN ISO 13934-1

min. 300.00 [N/5 cm]

Maximum tearing strength, cross direction (min.)

acc. to DIN EN ISO 13934-1

min. 1650.00 [N/5 cm]

We do not accept liability for errors. The confirmed properties are valid in the state of delivery. Any further processing can change them (e.g. washing / flame retardancy).

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Printing mistakes and changes are reserved.