



## Technical Data Sheet

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	80
Thickness	ISO 534	µm	106
Bulk	ISO 534		1,33
Moisture content	ISO 287	%	4,1
Roughness	ISO 8791	Bendtsen ml/min	220
Whiteness	ISO 11475	CIE	150
Brightness	ISO 2470-2	%	107
Opacity	ISO 2471	%	91



### References:

Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp

**Sylvamo Sweden AB**  
Nymöllavägen 260-15, 295 73  
Nymölla, Sweden  
Extract date: May 2023