




Fabric name	Polar Fleece-180
Fabric weight	180 ± 5 gsm
Composition	100% polyester
Full width	150 ± 2 cm
Weave	knitted
Finishes	antipilling
Application	workwear jackets or sport vests
Washing instruction	

Physical properties*

			warp	weft
1	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
2	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
3	Pilling Resistance, as received /after 2000 rubs	ISO 12945-2:2000	4	
4	Colour Fastness To Washing (cotton+polyester) 40°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	3-4	
5	Colour Fastness To Drycleaning, min.	ISO 105-D01:2010	4-5	
6	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4	
	Wet		4-5	
7	Colour Fastness To Organic Solvents	ISO 105-X05:1994	4-5	
8	Colour Fastness To Light	ISO 105-B02:2013	> 4	

* The values shown are indicative and may vary slightly from batch to batch.

XM TEXTILES EUROPE


Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com



**STANDARD
100**

**BEWO 084394
TESTEX**

**This certificate BEWO 084394 is valid until
15.08.2026.**

SUPPORTING DOCUMENTS

- ✓ Test report : BJ015 266840.1
- ✓ Declaration of conformity in accordance with EN ISO 17050-1 as required by OEKO-TEX®
- ✓ OEKO-TEX® Terms of Use (ToU)

A handwritten signature in blue ink, appearing to read "M. Bachmann", written over a horizontal line.

Matz Bachmann
Managing Director

A handwritten signature in blue ink, appearing to read "J. Kuchelmeister", written over a horizontal line.

Janine Kuchelmeister
Ecology Team Leader

Zurich, 2025-07-24