AB-1280-T
2021-0090
26.01.2021

TEST SONUÇLARI
The Results of The Tests

***Test Adı/** Test Name:* **Elektrostatik Özellikler – Yük Zayıflamasının Ölçülmesi (T)**

***İlgili Standart/** Relevant standard:* TS EN 1149-3:2004, Method 2

***Kondisyon Şartları/** Conditioning parameters:* 23±1 °C, %25±5 RH,

***Test Parametreleri/** Test parameters:* Test Şartları: 23±1 °C, %25±5 RH, Test Örneği: 3 adet, Ön İşlem: Uygulanmadı

Numune Adı	YFS-01			
Parametreler	1.Örnek	2.Örnek	3.Örnek	Ortalama
Kalkanlama Faktörü *Shielding Factor, S*	0,05	0,03	0,01	**0,03**
Yarılanma Süresi *Half Decay Time, t_{50}, s*	2,54	2,76	2,88	**2,73**

Numune Adı	YFS-03			
Parametreler	1.Örnek	2.Örnek	3.Örnek	Ortalama
Kalkanlama Faktörü *Shielding Factor, S*	0,03	0,02	0,00	**0,01**
Yarılanma Süresi *Half Decay Time, t_{50}, s*	2,61	2,68	3,15	**2,81**

Digitally signed by Cobzari-Țurcan Rodica
Date: 2022.02.25 09:04:39 EET
Reason: MoldSign Signature
Location: Moldova

"Sizlerle en üst düzeyde oluşmasına özen gösterdiğimiz tarafsız, güvenilir hizmet ve memnuniyetinizin sağlanabilmesi adına BUTEKOM web sitemizde yer alan *'BUTEKOM Laboratuvarları Müşteri Memnuniyeti Anketimizi'* doldurmanızı rica ederiz."

"We kindly ask you to fill out our '*BUTEKOM Laboratories Customer Satisfaction Survey*' on our BUTEKOM website in order to provide an objective, reliable service and satisfaction that we take care to reach at the highest level with you."

Testi Yapan/Yapanlar
Test Technician(s)

Fatma Nur İNAM

Y.F.S. GIDA TEM. AMBALAJ MEDİKAL TEKSTİL SAN.TİC.LTD.ŞTİ.

This report has been prepared in two originals, one to be given to the client and the other to be archived in the laboratory
BUTEKOM does not show or reproduce this report to third parties except authorized auditors of Turkish Accreditation Agency. The remaining samples after the report are destroyed after 3 years. The measurement results, comments and opinions given in the report belong only to the samples with the code number specified and can not be used for any other purpose. The report can not be partially copied and duplicated without the permission of the laboratory. Unsigned and unsealed reports are invalid