


Mechanic-280

100% COTTON
280 GSM / TWILL 3/1



Fabric name	Mechanic-280
Fabric weight	280 ± 5 gsm
Composition	100% Cotton
Full width	150 ± 2 cm
Weave	twill 3/1
Finishes	-
Area of use	multi seasonal workwear

Washing instruction



Physical properties*

			warp	weft	
1	Tensile strength, N	ISO 13934-1:2013	1000	500	
2	Tearing strength, N	ISO 13937-3:2000	30	28	
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%	
4	Abrasion Resistance	ISO 12947-2:2002	> 30 000		
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3-4		
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010			
			Colour change	3-4	
			Colour staining	3-4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013			
			Colour change	3-4	
			Colour staining	3-4	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001			
			Dry	3-4	
			Wet	2-3	
9	Colour Fastness To Light	ISO 105-B02:2013	> 4		

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com