

Oferta către RED-NORD

Echiprot SRL , Chisinau, Dacia 53/5									
Denumirea licitației: Achiziția Echipamentului individual de protecție									
Lot	Denumirea serviciilor	Unitatea de măsură	Cantitatea	Preț unitar (fără TVA)	Preț unitar (cu TVA)	Suma fără TVA	Suma cu TVA	Termenul de prestare/ zile	Termen de garanție de la producător
1	2	3	4	5	6	7	8	9	10
Lotul									
	Lot 3. Salopetă	un	787	345.84	415,00	272'170,84	326'605,00	30	365
	Total					272'170,84	326'605,00		

Data completării: 30.05.2024

SRL Echiprot Director

Vrabii C.



Fabric name	Builder-240
Fabric weight	240 ± 5 gsm
Composition	100% Cotton
Full width	150 ± 2 cm
Weave	twill 3/1
Finishes	—
Area of use	multi seasonal workwear

Washing instruction



Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1400	800
2	Tearing strength, N	ISO 13937-3:2000	29	22
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining	ISO 105-C06:2010	4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		3-4	
	Wet		2-3	
9	Colour Fastness To Light	ISO 105-B02:2013	> 4	

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com

SGS

Test Report

SL52035261736R01TX

Date July 02 2020

Page 1 of 3


SHANGHAI XM GROUP LTD
ROOM 2403, ZHONGYI INTERNATIONAL BUILDING 100 1833 NORTH ZHONGSHAN ROAD, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description (A) Woven fabric (BUILDER 240 - BUILDER 240 100% cotton 140 gsm)
Order: XM11-20-023

Composition (A) 100% cotton
Sample Color (A) Navy #002

Proposed Care Instruction



Sample Receiving Date

Jun 24 2020

Testing Period

Jun 29 2020 - Jul 02, 2020

Test Result(s)

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. For further details, please refer to the following page(s).

Test Performed

Selected test(s) as requested by applicant

Signed for and on behalf of
SGS CSTC Standards Technical Services (Shanghai) Co., Ltd. Testing Center

Hattie Chen

Hattie Chen (Account Executive)



SGS CSTC Standards Technical Services (Shanghai) Co., Ltd. Testing Center
100 1833 NORTH ZHONGSHAN ROAD, SHANGHAI 200003, CHINA
TEL: +86 (0)21 5891 9999 FAX: +86 (0)21 5891 9998
WWW.SGSCSTC.COM