


Unitec-240

65% POLYESTER / 35% COTTON
240 GSM / TWILL 2/1



Fabric name	Unitec-240
Fabric weight	240 ± 5 gsm
Composition	65% Polyester, 35% Cotton
Full width	150 ± 2 cm
Weave	twill 2/1
Finishes	—
Area of use	industrial workwear jackets, trousers and coveralls
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1400	660
2	Tearing strength, N	ISO 13937-3:2000	56	54
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 30 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining	ISO 105-C06:2010	4-5	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		3	
9	Colour Fastness To Light	ISO 105-B02:2013	4	

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com

XM Textiles

Unitec-240

65% POLIESTER / 35% BUMBAC

240 GSM / ȚESĂTURĂ CU BENZI DIAGONALE 2/1

Denumirea țesăturii	Unitec-240
Greutatea țesăturii	240 ± 5 gsm
Compoziție	65% poliester, 35% bumbac
Lățime completă	150 ± 2 cm
Țesătură	Țesătură cu benzi diagonale 2/1
Finisaje	-
Domenii de utilizare	jachete, pantaloni și salopete pentru îmbrăcăminte de lucru industrială
Instrucțiuni de spălare	<i>la se vedea originalul</i>

Proprietăți fizice*

			urzeală	bătătură
1	Rezistența la tracțiune, N	ISO 13934-1:2013	1400	660
2	Rezistența la rupere, N	ISO 13937-3:2000	56	54
3	Stabilitatea dimensională la spălare, max.	ISO 6330:2000	3.0%	3.0%
4	Rezistența la abraziune	ISO 12947-2:2002	> 30 000	
5	Rezistența la scămoșare (după 1000 rot.)	ISO 12945-2:2000	4	
6	Rezistența culorilor la spălare (bumbac+ poliester) la 60°C, min.	ISO 105-C06:2010		
	Schimbare de culoare	ISO 105-C06:2010	4-5	
	Pătrundere de culoare	ISO 105-C06:2010	4-5	
7	Rezistența culorilor la transpirație, min.	ISO 105-E04:2013		
	Schimbare de culoare		4-5	
	Pătrundere de culoare		4-5	
8	Rezistența culorilor la frecare, min.	ISO 105-X12:2001		
	Uscat		4-5	
	Umed		3	
9	Rezistența culorilor la lumină	ISO 105-B02:2013	4	

* Valorile afișate sunt orientative și pot varia ușor de la un lot la altul

www.xmtextiles.com

XM TEXTILES EUROPE

Str. Dariaus ir Gireno 42A, Camera 509
Vilnius, LT-02189, Lituania
Tel. +370 52 078 703
Email: info@xmtextiles.com

XM TEXTILES ROMÂNIA

Șos. Tamași 20, Hala 6B, Parter
Buftea, 070000, Ilfov, România
Tel. +40 31 630 3639
Email: info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross
40050 Funo di Argelato (BO), Bologna,
Italia
Tel. +39 051 952 8202
Email: info@xmtextiles.com

The undersigned, **Todorica Olesea**, authorized English language translator, certify the accuracy of the translation of the text, in witness whereof I apply my signature.

Subsemnata, **Todorica Olesea**, traduc tor autorizat de limb Englez , certific exactitatea traducerii cu textul înscrisului autentic, care a fost vizat de mine.

Data: 15.01.2025

Translator's seal:

/ Translator of English Language– TODORICA Olesea, Authorization AT no. 433 from June 27, 2013/

Semn tura traduc torului

Signature of translator



* * *

Aceast traducere a fost efectuat în cadrul Biroului de Traduceri "LICOLIN & CO" SRL , str.Bucure ti 59, of.7 or.Chi in u , Republica Moldova, de c tre traduc torul sus menționat.

This translation was done at the Agency of translation "LICOLIN & CO" Ltd, 59 Bucuresti Street, off. 7, Chisinau mun. , Republic of Moldova by the translator above mentioned.

